Nanocasting Route for the Synthesis of Ordered Mesoporous SnO₂ with Highly Crystalline Framework

Jusliha Juhari, Mohamad Zailani Abu Bakar and Ahmad Zuhairi Abdullah

School of Chemical Engineering, Engineering Campus, Universiti Sains Malaysia, Seri Ampangan, Nibong Tebal 14300, Seberang Perai Selatan, Pulau Pinang, Malaysia

Received: August 04, 2014 / Accepted: August 20, 2014 / Published: August 25, 2014.

Abstract: Ordered mesoporous metal oxides (OMMO) SnO₂ with large surface areas and highly crystalline frameworks were successfully synthesized via nanocasting routes using 3D cubic ordered mesoporous silica KIT-6 templates. The chemical and structural properties of these materials were characterized by means of XRD, N₂ adsorption-desorption SEM and TEM analyses. The present work revealed that the mesoporous SnO₂ materials exhibited well-defined and long-range periodic order of mesopores as well as highly crystalline frameworks, indicating successful replication from the mesoporous KIT-6 silica templates. Moreover, these materials demonstrated high surface area of 109 m²/g and high pore volume of 0.22 cm³/g as well as large pore size of 6.2 nm. Hence, the nanocasting route offers a versatile and simple way of creating ordered mesoporous SnO₂ with enhanced properties that may have potential applications in the field of catalysis and gas-sensing.

Key words: Mesoporous material, metal oxide, nanocasting, SnO₂, KIT-6 silica.

1. Introduction

Since the discovery of ordered mesoporous materials in 1992 [1], interests in the research field have tremendously expanded, especially with regards to their syntheses and structural characterizations. The unique properties of ordered mesoporous materials such as high surface area and uniform pore size as well as tuneable pore structure, geometries and compositions have attracted more attention in various applications. Recently, the research direction of these materials has been shifted from silica-based materials to non-siliceous metal oxide materials, which are expected to be more useful for a wide range of applications such as catalysis, adsorption, separation, electrochemical, electronic and optical device [2-5].

Soft templating method, which employs organic surfactants as structure directing agents has been

effectively used to synthesize mesoporous metal oxides with improved long-range orders. However, many mesoporous metal oxides prepared from this method give a lot of disadvantages, such as amorphous inorganic walls, poor mesoporous structure and thermal instability during the removal of organic templates. The amorphous pore walls of most mesoporous metal oxides, which have poor thermal and mechanical stability, restrict the range of applications of these materials [6]. Crystallized wall structure is expected to provide better thermal and mechanical stability as well as superior electric and optical properties [7]. The crystallization and crystallinity of mesoporous metal oxides have therefore fascinated many attentions.

An alternative way to produce mesoporous metal oxides is via the nanocasting method (Fig. 1), where mesoporous silica materials are utilized as the hard templates [8]. Typically, a precursor solution for the targeted metal oxide is infiltrated into the mesopores of

Corresponding author: Mohamad Zailani Abu Bakar, Ph.D., associate professor, research fields: process safety and modelling, environmental. E-mail: chmohdz@usm.my.

Fig. 1 Schematic illustration of the nanocasting route. Adapted from Ref. [4].

the silica templates. After drying the solvent, the composite is heated at a certain temperature in order to convert the precursor into oxide. The silica template is finally removed by chemical treatment using hydrofluoric acid (HF) or sodium hydroxide (NaOH), yielding mesoporous metal oxides as its negative replica. This approach provides the opportunity to prepare mesoporous metal oxides with promising properties due to high crystalline frameworks, high specific surface areas, regular mesopore arrangements and thermally stable. The first example of porous crystals of metal oxides that have been successfully synthesized via this method was demonstrated by Zhu et al. in 2003 [9]. To date, many publications related to the porous crystal of metal oxides have been reported.

Among various metal oxides, SnO₂ with a wide band gap ($E_g = 3.6$ eV) is one of the most attractive materials in the applications of gas sensing, catalysis, energy conversion and optoelectronic materials [10]. SnO₂ in the form of mesoporous structures can be a promising candidate for these applications because they retain large specific surface areas and provide efficient gas transport through highly organized pores of 2–50 nm in diameter [11]. However, there are still inadequate studies that focus on the crystalline structures of these materials, since many applications require crystalline materials. Thus, it would be advantageous to synthesize ordered mesoporous SnO₂ with desired crystalline frameworks.

In the present work, a series of ordered mesoporous SnO₂ materials have been synthesized via nanocasting route using three-dimensional (3D) cubic ordered mesoporous silica (KIT-6) as a hard template. To the best of our knowledge, for the first time, tin (II)

chloride dehydrate used as a metal-containing precursor has been introduced into the silica KIT-6 pores by a “vacuum assisted” impregnation method. Through this method, large surface area and highly ordered mesostructure with a crystalline framework of mesoporous SnO₂ material has been obtained. The quality of the 3D cubic silica KIT-6 template and its replicated SnO₂ material has been evaluated and characterized. The successful structure replication of SnO₂ material from KIT-6 template will be discussed in detail in the next section.

2. Materials and Methods

2.1 Chemicals

Triblock copolymer (Pluronic P123 (MW) 5800, EO₂₀PO₇₀EO₂₀) was purchased from Aldrich Corporation. Tetraethylorthosilicate (TEOS, 98%), tin chloride (SnCl₂·2H₂O), sodium hydroxide (NaOH), hydrochloric acid (HCl, 37%), n-butanol (n-BuOH) and ethanol (C₂H₅OH) were obtained from Merck. All chemical reagents and solvents were of analytical grade and used without further purification. Distilled and deionized water was used throughout this work.

2.2 Synthesis of the Hard Template

Cubic ordered mesoporous silica KIT-6 was synthesized in acidic conditions according to a previous reported procedure with a slight modification [12]. In a typical synthesis procedure, 5 g of P123 was dissolved in 180 mL distilled water and 10 g of concentrated HCl. The mixture was stirred for 3 h at 35 °C and then 5 g of n-butanol was added with continuous stirring for another hour. After that, 11 g of TEOS was added and stirred for 24 h at the same temperature. The resulting mixture was then aged in oil bath for 24 h at 80 °C under static condition (hydrothermal treatment). Finally, the white solid was recovered by filtration, washed with deionized water and dried overnight in an oven at 100 °C. Thereafter, the products were calcined in air at 500 °C for 6 h at a heating rate of 2 °C min⁻¹ in order to remove the

organic template.

2.3 Nanocasting Synthesis of the Mesoporous SnO₂

For the synthesis of the mesoporous SnO₂, KIT-6 silica template was used as a template and performed according to the “vacuum assisted” impregnation method as reported previously by Liu and coworkers [13]. Typically, 2 g of KIT-6 and 3.25 g of SnCl₂·2H₂O were dispersed in 50 mL of ethanol. After 1 h of stirring, ethanol was removed through evaporation by heating the mixture at 50 °C and 0.1 bar in a vacuum oven for 6 h. The resulting powder was then calcined in a furnace at a heating rate of 2 °C/min from room temperature to 450 °C and maintained at this temperature for 3 h until all chloride species was completely decomposed. The impregnation and decomposition steps were repeated, following the same conditions in order to achieve higher loadings. Finally, the silica template was removed at room temperature using a 2 M NaOH aqueous solution for 3 h. The SnO₂ materials were then recovered by centrifugation, washed twice with water and dried at 100 °C overnight. Reproducibility of the preparation was checked by repeating the synthesizing procedure for several batches.

2.4 Material Characterization

Small-angle and wide-angle powder X-ray diffraction (PXRD) patterns were recorded using a Bruker AXS D8 ADVANCE and Philips PW 1710 diffractometer equipped with Cu K α X-ray source at 30 kV and 40 mA, respectively. Scanning electron microscope (SEM) images were taken by means of a Quanta FEG450 microscope operating at an accelerating voltage of 5 kV under high vacuum. Transmission electron microscope (TEM) images were obtained using a FEI/Philips CM 12 microscope with an acceleration voltage of 80 kV. Nitrogen adsorption-desorption isotherms were measured using a Micromeritics ASAP 2020 analyzer at liquid nitrogen temperature (77 K). Prior to the analysis, the samples

were degassed at 300 °C in vacuum for 8 h. The Brunauer-Emmett-Teller (BET) specific surface area was calculated using the adsorption data in a relative pressure (P/P₀) range from 0.05 to 0.3, and the total pore volume was determined from the amount adsorbed at P/P₀ = 0.98. The pore-size distribution curve was calculated based on the desorption branch of the isotherm using the Barrett-Joyner-Halenda (BJH) method. The pore diameter is defined as the position of the maximum peak in the pore-size distribution.

3. Results and Discussion

3.1 XRD Analysis

Fig. 2a shows the small-angle PXRD patterns of the mesoporous silica KIT-6 template and the respective template-free mesoporous SnO₂ material obtained from the nanocasting route. The XRD patterns indicate that the mesostructure of SnO₂ material is quite similar to that of KIT-6 silica. The mesoporous silica KIT-6 present the 3D cubic (Ia3d) mesostructure, which can be indexed to [211], [220], and [321] reflections as shown in Fig. 2a. The obtained template-free mesoporous SnO₂ clearly show well-resolved diffraction peak at [211] reflection, indicating that the pore symmetry was successfully replicated. However, the mesoporous SnO₂ material exhibited a somewhat broader and less well-resolved diffraction peak at [321] reflection, which indicated a slightly lower overall mesostructural order as frequently found in nanocasted materials [2, 14]. The unit-cell parameter of the mesoporous SnO₂ material calculated from the position of the [211] reflection is about 22.5 nm, which is in fair agreement with the value of 23.3 nm for the mesoporous silica KIT-6 template as shown in the Table 1.

The wide-angle PXRD patterns of the SnO₂/KIT-6 composite and the template-free mesoporous SnO₂ material are illustrated in Fig. 2b. It can be seen that the framework structures for both samples are highly crystalline and display well-resolved diffraction peaks for SnO₂ nanocrystals that can be indexed to a tetragonal

Fig. 2 (a) Small-angle PXRD patterns of mesoporous silica KIT-6 template and template-free mesoporous SnO₂ material. (b) Wide-angle PXRD patterns of SnO₂/KIT-6 composite and template-free mesoporous SnO₂ material.

Table 1 Structural properties of as-prepared mesoporous samples.

Sample	S_{BET} (m ² /g)	V_{T} (cm ³ /g)	D (nm)	d_{211} (nm)	1a_0 (nm)	2W (nm)
Silica KIT-6 template	755	0.94	5.3	9.5	23.3	6.3
SnO ₂ /KIT-6 composite	265	0.25	4.8	9.4	23.0	6.7
SnO ₂ material	109	0.22	6.2	9.2	22.5	5.1

$$^1a_0 = d_{211}\sqrt{6}, \quad ^2W = a_0/2 - D.$$

cassiterite structure [15] (JCPDS No.: 41-1445, $P4_2/mnm$). All the XRD patterns show broad peaks, and there are no major differences before and after the silica removal as reported by Shon et al. [16]. These

results indicated that the frameworks of SnO₂ material were formed within the confined mesopores of KIT-6 silica during the infiltration process in vacuum condition, and the nanostructured frameworks formed were maintained even after the silica removal. The average crystalline domain sizes calculated using the Scherrer equation were estimated to be 4.9 nm and 5.3 nm for the SnO₂/KIT-6 composite and template-free mesoporous SnO₂ material, respectively, which were comparable to the pore sizes of KIT-6 silica templates. Moreover, there were no features of SiO₂ or NaOH diffraction peaks found in the SnO₂ material after the leaching process, which suggested a successful removal of silica and no reaction occurred between either the silica or sodium with the SnO₂ material.

3.2 N₂ Adsorption-Desorption Analysis

The mesostructure of the SnO₂ material was further confirmed in the N₂ adsorption/desorption analysis. Fig. 3a shows the N₂ adsorption-desorption isotherms of the mesoporous silica KIT-6 template, SnO₂/KIT-6 composite and the corresponding template-free mesoporous SnO₂ material. It can be observed that the mesoporous silica KIT-6 template and SnO₂/KIT-6 composite show a type-IV isotherm with H1 hysteresis. The gradual filling of the silica pores with SnO₂ is confirmed by a significant decrease in the amount of the adsorbed nitrogen volume. The template-free mesoporous SnO₂ material exhibited type-IV isotherms with a capillary condensation step occurring in the relative pressure (P/P_0) range of 0.6-0.9. This indicates that the mesostructure of SnO₂ material exhibited well-defined and confirmed the existence of uniform mesopore in their structures.

The pore size distributions of the mesoporous silica KIT-6 template, SnO₂/KIT-6 composite and the corresponding template-free mesoporous SnO₂ material calculated from the desorption isotherm by the BJH method are depicted in Fig. 3b. Narrow pore size distributions of the mesoporous silica KIT-6 template and the respective SnO₂/KIT-6 composite was

Fig. 3 (a) N₂ adsorption/desorption isotherms and (b) the corresponding BJH pore size distribution curves of mesoporous silica KIT-6 template, SnO₂/KIT-6 composite and template-free mesoporous SnO₂ material.

with diameter of ~5 nm are observed. As shown in Fig. 3b, the highest peak does not significantly shift from KIT-6 silica template to SnO₂/KIT-6 composite, indicating that the growth of SnO₂ crystals occurred predominantly along the pore axis. However, the template-free mesoporous SnO₂ material demonstrated dual porous structures (~6 nm and ~11 nm). The first is expected from the KIT-6 silica framework (~6 nm) after the replication process, and the second (~11 nm)

might be generated by the structural transformation from the cubic Ia3d mesostructure to the tetragonal I4₁/a (or lower) mesostructure [16].

The surface and structural properties including BET specific surface area (S_{BET}), total pore volume (V_T), pore size (D), d spacing at [211] reflection (d_{211}), unit cell-parameter (a_0) and pore wall thickness (W) of the samples are listed in Table 1. The mesoporous silica KIT-6 template exhibited a surface area of 755 m²/g, a total pore volume of 0.94 cm³/g and a pore size of 5.3 nm, while the SnO₂/KIT-6 composite showed a much smaller surface area and a total pore volume of 265 m²/g and 0.25 cm³/g, respectively. The pore size, however, only slightly decreased to 4.8 nm. This is due to the vacancies that reappeared in the pore which was previously filled with the precursor solution after the crystallization of SnO₂ material. The template-free mesoporous SnO₂ material displayed a surface area of 109 m²/g, a total pore volume of 0.22 cm³/g and a pore size of 6.2 nm, which are consistent with those reported earlier [15–17]. The decrease in surface area as well as total pore volume of the SnO₂/KIT-6 composite and template-free mesoporous SnO₂ material in comparison with mesoporous silica KIT-6 templates were due to both the crystalline nature of the oxide materials as well as their higher bulk densities [18].

Theoretically, the pore size (D) of the nanocasted material should be the same as the pore wall thickness (W) of the structure template and vice versa [19]. In the present study, the calculated wall thickness of mesoporous silica KIT-6 template and the corresponding template-free mesoporous SnO₂ material are 6.3 and 5.1 nm, respectively. It can be noticed that the pore wall thickness of mesoporous silica KIT-6 template is very similar to the pore size of mesoporous SnO₂ material of 6.2 nm. This suggested that the filling of silica KIT-6 pores with SnO₂ material has been successfully completed.

3.3 SEM and TEM Analysis

Figs. 4a–4f show representatives SEM and TEM

Fig. 4 SEM and TEM images of mesoporous silica KIT-6 template (a, b), SnO₂/KIT-6 composite (c, d) and template-free mesoporous SnO₂ material (e, f).

Images for the mesoporous silica KIT-6 template, composite material and the corresponding template-free mesoporous SnO₂ material. It can be clearly seen that the SnO₂/KIT-6 composite and template-free mesoporous SnO₂ material are very similar to those of mesoporous silica KIT-6 template and exhibited uniform particle morphologies. The template-free mesoporous SnO₂ material demonstrated well-defined, long-range, periodic and ordered mesopore as well as highly crystalline framework, indicating the successful replication from the mesoporous silica KIT-6 template. These results coincide with the data of PXRD patterns and N₂

adsorption-desorption isotherms.

4. Conclusions

Mesoporous SnO₂ material has been successfully nanocasted from mesoporous KIT-6 silica template with large surface area, periodically ordered and highly crystalline framework via nanocasting route. The mesopores of silica templates could be infiltrated merely by stirring them with tin precursor (SnCl₂·2H₂O) in ethanol solution followed by evaporation of ethanol at 50 °C in vacuum condition. The mesostructures and morphologies of the silica KIT-6 templates are basically maintained in the mesoporous SnO₂ materials after the template removal. This nanocasting route is able to be exploited as a facile method for the preparation of mesoporous SnO₂ created with periodically ordered and highly crystalline framework, which has good potentials for various practical applications such as catalysis and gas sensing.

Acknowledgments

The authors gratefully acknowledge the financial support by Universiti Sains Malaysia (USM) through the FRGS-Grant (Project No.: 6071250) and the Ministry of Education Malaysia, through MyPhD Fellowship scheme to the first author.

References

- [1] C.T. Kresge, M.E. Leonowicz, W.J. Roth, J.C. Vartuli, J.S. Beck, Ordered mesoporous molecular sieves synthesized by a liquid-crystal template mechanism, *Nature* 359 (1992) 710-712.
- [2] H. Tuysuz, M. Comotti, F. Schuth, Ordered mesoporous Co₃O₄ as highly active catalyst for low temperature CO-oxidation, *Chemical Communications* 0 (2008) 4022-4024.
- [3] P. Wang, I. Lo, Synthesis of mesoporous magnetic Y-Fe₂O₃ and its application to Cr (VI) removal from contaminated water, *Water Research* 43 (2009) 3727-3734.
- [4] J.Y. Luo, J.J. Zhang, Y.Y. Xia, Highly electrochemical reaction of lithium in the ordered mesoporous β-MnO₂, *Chemistry of Materials* 18 (2006) 5618-5623.
- [5] Y. Wan, H. Yang, D. Zhao, General synthesis of ordered

- nonsiliceousmesoporous materials, *Biomolecular Catalysis* 986 (2008) 2-48.
- [6] H. Yang, D. Zhao, Synthesis of replica mesostructures by the nanocasting strategy, *Journal of Materials Chemistry* 15 (2005) 1217-1231.
- [7] T. Katou, B. Lee, D. Lu, J.N. Kondo, M. Hara, K. Domen, Crystallization of an ordered mesoporousNb-Ta oxide, *Angewandte Chemie International Edition* 42 (2003) 2382-2385.
- [8] H. Lu, F. Schüth, Nanocasting: A versatile strategy for creating nanostructured porous materials, *Advanced Materials* 18 (2006) 1793-1805.
- [9] K. Zhu, B. Yue, W. Zhou, H. He, Preparation of three-dimensional chromium oxide porous single crystals templated by SBA-15, *Chemical Communications* 0 (2003) 98-99.
- [10] A. Dieguez, A. Romano-Rodriguez, J.R. Morante, L. Sangaletti, L.E. Depero, E. Comini, et al., Influence of the completion of oxidation on the long-term response of RGTO SnO₂ gas sensors, *Sensors and Actuators B: Chemical* 66 (2000) 40-42.
- [11] J.H. Pan, S.Y. Chai, C. Lee, S.E. Park, W.I. Lee, Controlled formation of highly crystallized cubic and hexagonal mesoporous SnO₂ thin films, *The Journal of Physical Chemistry C* 111 (2007) 5582-5587.
- [12] F. Kleitz, S.H. Choi, R. Ryoo, Cubic Ia3d large mesoporous silica: Synthesis and replication to platinum nanowires: carbon nanorods and carbon nanotubes, *Chemical Communications* 0 (2003) 2136-2137.
- [13] H. Liu, X. Du, X. Xing, G. Wang, S.Z. Qiao, Highly ordered mesoporous Cr₂O₃ materials with enhanced performance for gas sensors and lithium ion batteries, *Chemical Communications* 48 (2011) 865-867.
- [14] Y. Ren, F. Jiao, P.G. Bruce, Tailoring the pore size/wall thickness of mesoporous transition metal oxides, *Microporous and Mesoporous Materials* 121 (2009) 90-94.
- [15] H. Kim, J. Cho, Hard templating synthesis of mesoporous and nanowire SnO₂ lithium battery anode materials, *Journal of Materials Chemistry* 18 (2008) 771-775.
- [16] J.K. Shon, S.S. Kong, Y.S. Kim, J.H. Lee, W.K. Park, S.C. Park, et al., Solvent-free infiltration method for mesoporous SnO₂ using mesoporous silica templates, *Microporous and Mesoporous Materials* 120 (2009) 441-446.
- [17] T. Waitz, B. Becker, T. Wagner, T. Sauerwald, C.D. Kohl, M. Tiemann, Ordered nanoporous SnO₂ gas sensors with high thermal stability, *Sensors and Actuators B: Chemical* 150 (2010) 788-793.
- [18] J.H. Smatt, N. Schuwer, M. Jarn, W. Lindner, M. Linden, Synthesis of micrometer sized mesoporous metal oxide spheres by nanocasting, *Microporous and Mesoporous Materials* 112 (2008) 308-318.
- [19] T. Wagner, T. Sauerwald, C.D. Kohl, T. Waitz, C. Weidmann, M. Tiemann, Gas sensor based on ordered mesoporous In₂O₃, *Thin Solid Films* 517 (2009) 6170-6175.