Local Microstructural Stability and Hydrogen Embrittlement of Iron-Base FCC Alloys

Robert Fussik* and Sebastian Weber

Lehrstuhl für Neue Fertigungstechnologien und Werkstoffe, Bergische Universität Wuppertal, Bahnhofstr. 15, D-42651 Solingen, Germany

Abstract: In the frame of this work, the influence of microsegregations on local properties of certain austenitic steels is investigated. One intention is to generate “property-maps” dependent on the local chemical composition, more specifically, the local concentration of alloying elements. Previous studies exhibited that the steel AISI 304L is susceptible to hydrogen embrittlement whereas AISI 316L features a high resistance to the embrittlement process by atomic hydrogen. These results are partly connected with the positive influence of the element Ni on the austenite stability. In addition, the value of the stacking fault energy (SFE) affects the deformation mechanism during plastic strain. A low SFE is related with an increase in strength due to the twinning process or an ϵ - and α' -martensite transformation, respectively. Austenitic (γ) steels with a low SFE tend to transform in the order $\gamma \rightarrow \epsilon \rightarrow \alpha'$. On the other hand, austenitic steels with a high SFE show a high resistance to α' -transformation due to the more difficult direct $\gamma \rightarrow \alpha'$ transformation. Local concentration differences of alloying elements (microsegregation) lead to an inhomogeneous response during plastic deformation, because of the resulting differences in the local SFE and the local austenite stability. Based on a fundamental knowledge about the local deformation mechanisms, it will be possible to develop new austenitic multicomponent iron-based fcc alloys with a high resistance to hydrogen environment embrittlement. The development of these alloys is focused on the microstructural stability. In this work, measured and calculated results of microsegregations in iron-base fcc alloys are presented. They serve as a basis for calculated local properties which will be discussed in the context of hydrogen embrittlement.

Key words: Austenitic stainless steel, local austenite stability, stacking fault energy (SFE), segregations, secondary cracks.

1. Introduction

Fossil fuels are the primary energy source for the energy economy and automotive industry. Especially, the efficiency of utilization of fossil fuel has increased over the years. However, the availability of fossil fuel is limited. Oil is the most important fossil energy source. The combustion of oil leads to the emission of CO₂ which is responsible for global warming due to greenhouse gas. Currently, there are two ways to achieve the goal of zero local emission. Firstly, by using battery-driven electrical engines and secondly, by using hydrogen as engine fuel. Both technical possibilities possess different disadvantages. Compared to conventional combustion engines electrical engines provide much smaller range due to

their battery capacity. Otherwise, engines which use hydrogen as fuel are stressed by hydrogen itself. Atomic hydrogen at high pressure in metallic tanks and gas pipes (transport system for hydrogen) may lead to an embrittling effect.

Another aspect is the sustainable energy generation. A sustainable energy generation can be realized by renewable energy which includes wind energy, photovoltaics, biomass, tidal or the combination of them [1]. In this context, the generation of hydrogen and its storage are often mentioned [2]. Hydrogen storage under high pressure or cryogenic temperature increases the capacity. Focused on hydrogen, the detrimental impact of solute atomic hydrogen in steels must be considered.

Applications in respect of power generation, storage and transport of liquid or gaseous hydrogen depend on a suitable choice of applicable material. In general,

*Corresponding author: Robert Fussik, Prof. Dr.-Ing., research field: materials science and engineering.

these materials are stressed by chemical (corrosion), thermal (temperature) and/or mechanical (pressure) impact. Several components of stationary facilities or mobile applications are in a permanent contact with fuel. For instance, tanks are used to storage, valves adjust the fuel-flow and pipelines are used for the transport.

In this regard, austenitic stainless steels are commonly used for hydrogen applications. The beneficial properties in respect of corrosion resistance and ductility also at low temperature are the reasons for the good compatibility of austenitic steels. Nevertheless, austenitic stainless steels are susceptible to hydrogen embrittlement [3]. In particular, metastable austenitic steels such as AISI 304 show an embrittling effect during plasticity in hydrogen atmosphere [4]. Strain induced martensite transformation ($\gamma \rightarrow \alpha'$) during plastic deformation changes the properties of metastable austenitic steels. The combination of hydrogen atmosphere and phase transformation of metastable austenitic steels is related to their susceptibility to hydrogen embrittlement. The stability of the austenitic phase is an important characteristic of austenitic stainless steels in terms of their resistance to hydrogen environment embrittlement [5-8]. In this context, the prevention of the formation of α' -martensite is necessary [5, 6, 9]. In this regard, austenite formers such as Ni are important to suppress the formation of α' -martensite [10]. Previous investigations of metastable austenitic steels describe a relation between a low stacking fault energy (SFE) and the deformation induced formation of martensite. Thereby, a direct transformation of austenite to α' -martensite appears at a high SFE, whereas a low SFE is responsible for an indirect martensite transformation in the sequence of $\gamma \rightarrow \epsilon \rightarrow \alpha'$ [11]. Concerning hydrogen embrittlement, the formation of ϵ -martensite by stacking faults has no detrimental effect [12, 13].

For the estimation of the austenite stability empirical equations or in-situ calculations may be

used. The results of such calculations refer only to the global alloy composition [14-17], while local concentration differences in form of microsegregations are disregarded. A recent study considered local variations of Cr and Ni contents of a conventionally manufactured steel grade AISI 316L by EDS investigation of segregations bands [18]. This investigation showed that differences in chemical composition in form of segregations affect the stability of austenite [18]. Especially, the segregation of the austenite former Ni may well influence the local properties of an metastable austenitic steel. Therefore, the focus of this work is the investigation of microsegregation and to deduce from the results a predication of the local stability of the examined alloy.

In the context of hydrogen environment embrittlement, investigations of specimens examined in hydrogen atmosphere by tensile tests show a distinct formation of secondary surface cracks [4]. The formation of secondary cracks is related to the influence of atomic hydrogen in austenitic steels [10]. The local occurrence of strain-induced martensite benefits the formation of secondary cracks [10]. In this context, the stability of austenite against the local formation of martensite is an important parameter. Therefore, secondary surface cracking of a specimen which was examined by tensile test in hydrogen atmosphere will be discussed in the context of local stability of the austenite.

2. Experimental

2.1 Specimens and Tensile Tests

Specimen of former investigations of Martin [19] were used for the microstructural study of this work. The production route of these sample is described below.

Bars of conventional manufactured AISI 304L (X2CrNi18-8) with a diameter of 30 mm were used to produce tensile specimens with a length of 30 mm and a diameter of 5 mm. Tensile specimens were machined out from the center of the bars. Afterwards,

heat treatment was performed in a vacuum furnace at 1,050 °C for 30 min. As quenching medium argon was used at a pressure of 0.2 MPa to avoid oxidation and distortion of the tensile specimens.

Tensile tests were performed in pure hydrogen gas with a purity of more than 99.9999 % and a pressure of 40 MPa. According to ASTM G129 standard an initial strain rate of $5.5 \times 10^{-5} \text{ s}^{-1}$ was used. In addition, the experimental temperature in hydrogen atmosphere was -50 °C to induce a maximum embrittlement in a hydrogen atmosphere [20].

2.2 Analysis of Microsegregations

Microstructure, propagation of secondary surface cracks and gradients in chemical composition were analyzed by scanning electron microscope (SEM) (Tescan Vega3 SBH). Characterization of the local element distribution (microsegregations) were carried out by energy dispersive X-ray spectrometry (EDS) using an Bruker Quantax EDS-system (XFlash 5030 detector). Microsegregations were examined by EDS line scans and EDS mappings. The determination of the distribution of the main alloying elements (Cr, Ni) were performed without consideration of carbon and nitrogen, whereas substitutional elements with a content greater than 0.1 mass% were considered. For the EDS investigations an acceleration voltage of 25 kV and a working distance of 15 mm were used. The measurement time for EDS line scans was about 40 min for a length of approximately 100 µm (beam diameter of 120 nm, step distance of 300 nm). EDS

$$M_{d30}(\text{°C}) = 551 - 462(C + N) - 9.2Si - 8.1Mn - 13.7Cr - 29(Ni + Cu) - 18.5Mo - 68Nb - 1.42(GS - 8.0) \quad (3)$$

where, M_{d30} means the temperature at which 50 vol.% of the austenite transforms to martensite by a plastic strain of 30 % and GS is the grain size number according to ASTM E112. The calculation of the M_{d30} temperature is performed by input of alloying elements in mass%.

A quantitative determination of the interstitial elements C and N by means of EDS-analysis is not

mappings were carried out for 8 h at least and a beam diameter of 180 nm was used. The micrographs were taken with secondary electrons contrast.

2.3 Estimation of Global and Local Austenite Stability

Thermo-Calc software (TC), version TCS, and the thermodynamic database TCFe7 were used for calculation of the stacking fault energy (SFE) and the difference in Gibbs free energy between the austenitic fcc- (γ) and ferritic (martensitic) bcc-phase (α). Both parameter were used to evaluate the local stability of austenite.

Corresponding to works of Mújica *et al.* [14, 15] the SFE-calculation was carried out based on the model of Olsen &Cohen (Eq. (1)) [21].

$$SFE = \frac{2 \cdot \Delta G^{fcc \rightarrow hcp}}{\sqrt[3]{V_m^2 N_0}} + 2 \cdot \sigma^{\gamma/\varepsilon} \quad (1)$$

where, $\Delta G^{fcc \rightarrow hcp}$ is the difference in Gibbs free energy of the γ - and ε -lattice, V_m means the molar volume, N_0 is the Avogadro constant and $\sigma^{\gamma/\varepsilon}$ is the interfacial energy between a stacking fault (SF) and the undisturbed lattice of the metal matrix.

Calculation of the driving force for $\gamma \rightarrow \alpha$ -transformation was used to determine the austenite stability (Eq. (2)).

$$\Delta G^{\gamma \rightarrow \alpha} = G^{bcc} - G^{fcc} \quad (2)$$

where, G^{bcc} and G^{fcc} are the Gibbs free energies of the bcc- or fcc-phases, respectively.

In addition, an empirical equation according to Nohara, was used to estimate the local stability of austenite against martensitic transformation (Eq. (3)) [22].

possible, therefore, the content of C and N was assumed to be constant. Consequently, microsegregations of C and N are not considered in the calculations of this work.

3. Results

3.1 Global Alloy Composition and Global Properties

Optical emission spark spectrometry (OES) was

used to measure the global chemical composition of the tensile test specimens. Analyzed was the cross section in as-received condition of the conventional steel grade AISI 304L by several measurements. The measured alloy composition in mass%, the calculated M_{d30} temperature (Eq. (3)) and difference in Gibbs free energy between the γ - and α -phase (Eq. (2), $\Delta G^{\gamma \rightarrow \alpha}$) for the global alloy composition are given in Table 1. For the calculation of the M_{d30} temperature a grain size number of 6 ($46 \pm 6 \mu\text{m}$), according to ASTM E 123, was determined.

3.2 EDS Line Scan Analysis and Local Properties

The results of EDS analysis are divided into characterization by line scans and mappings. Thereby, all substitutional elements listed in Table 1 were considered. The distribution of the interstitial elements C and N were considered as homogeneous. Fig. 1 shows the results of two EDS line scans (LS1 and LS2), with a length of approximately $100 \mu\text{m}$, near the area of crack initiation and crack-end. The EDS line scans start at the borderline of the embedding and the analyzed tensile test specimen, perpendicular to the specimen surface. To ensure that the specimen surface is analyzed, the measurement started in embedding (first 3-4 μm , Fig. 1).

Fig. 1a illustrates an inhomogeneous distribution of the main alloying elements Cr and Ni, whereas the level of Mn seems to be constant with a content of 2 mass%. The Cr concentration varies in a range of 3 mass% (18-21 mass%). The greatest difference in distribution is indicated by the Ni concentration. The Ni content fluctuates between 6 and 11 mass%. Both diagrams in Fig. 1a show that the crack stops (dashed line) in areas with a high or increasing Ni content.

Both graphs in Fig. 1b illustrate the course of the

local austenite stability dependent on the chemical composition along the analyzed EDS line scan path. Displayed are the calculated values, by using EDS data, of M_{d30} temperature (empirical equation) and Gibbs free energy difference $\Delta G^{\gamma \rightarrow \alpha}$ (using TC database) between the α - and γ -phase. The values of the M_{d30} temperature (black line in Fig. 1b) and $\Delta G^{\gamma \rightarrow \alpha}$ (grey line in Fig. 1b) illustrate the stability of austenite by means of temperature or Gibbs free energy, respectively. By trend, both graphs show a reverse curve progression. Associated with the evolution of the Ni content in Fig. 1a, with increasing Ni content the M_{d30} temperature decreases, while the $\Delta G^{\gamma \rightarrow \alpha}$ value increases. The crack propagation is stopped in regions with a M_{d30} temperature range of -20 to $-30 \text{ }^\circ\text{C}$ and a $\Delta G^{\gamma \rightarrow \alpha}$ of approximately $-2,500 \text{ J/mol}$ (Fig. 1b).

The graphs in Fig. 1c are divided by means of the height of SFE depending on the deformation mechanism. The classification of the deformation mechanism in dependence of the SFE takes place in accordance with the investigations of Allain *et al.* and Dumay *et al.* [23, 24]. Therefore, dislocation glide appears at a SFE above 35 mJ/m^2 , TWinning induced plasticity (TWIP) occurs below 35 mJ/m^2 up to 18 mJ/m^2 , between 18 and 12 mJ/m^2 exists a range of TRansformation Induced Plasticity (TRIP) characterized by ϵ -martensite (hcp-lattice) formation and below 12 mJ/m^2 a TRIP region of α' -martensite (bcc-lattice) is present.

Contrary to the M_{d30} temperature and $\Delta G^{\gamma \rightarrow \alpha}$ in Fig. 1b, the calculated SFE in Fig. 1c does not indicate a direct correlation with the course of the Ni content in Fig. 1a. Fig. 1c implies that the crack propagation is stopped in the TRIP region of ϵ -martensite formation with a SFE above 12 mJ/m^2 .

Table 1 Chemical composition of tensile test specimens, values given in mass-% (without trace-elements). Calculated M_{d30} temperature in $^\circ\text{C}$ and difference in Gibbs free energy $\Delta G^{\gamma \rightarrow \alpha}$ in J/mol . Global analysis measured by OES, local analysis measured during EDS mapping.

304L	C	N	Cr	Ni	Mn	Si	Cu	Mo	M_{d30}	$\Delta G^{\gamma \rightarrow \alpha}$
OES	0.02	0.07	17.7	8.6	1.9	0.7	0.6	0.3	-27	-2430
EDX	-	-	18.4	8.0	1.7	1.2	0.6	0.5	-	-

Fig. 1 EDS line scans (LS): (a) distribution of the main elements Cr (black dotted line), Ni (black line) and Mn (grey line), (b) calculated M_{d30} temperature (black line) and difference in Gibbs free energy $\Delta G^{\gamma \rightarrow \alpha}$ (grey line) and (c) calculated SFE along the measuring lines LS1 and LS2. The calculations in (b) and (c) were carried out in consideration of all elements of Table 1.

3.3 EDS Mapping and Local Property Maps

The EDS mapping in Fig. 2 shows the investigated area of secondary cracks. Depicted is the distribution

of the alloying elements Cr and Ni. Zones of segregation are clearly visible by the Cr distribution as well as by the Ni distribution. The width of the segregation bands of Ni (high and low Ni-content) is

approximately 50 μm . In contrast, the segregation bands of Cr are significantly smaller. In comparison to the microsegregation of Cr, the segregation of the element Ni is more pronounced. As illustrated by means of the EDS mapping of the Ni content, the

crack propagation stops in front of the segregation line which exhibits a Ni content of about 8 mass%.

Fig. 3 shows the calculated property maps, based on the data of EDS mappings. In Fig. 3a, the calculated M_{d30} temperature map with the associated histogram,

Fig. 2 EDS mapping of commercial AISI 304L steel in the area of secondary cracks. Measurement of the main alloying elements Cr and Ni in mass%.

Fig. 3 Calculated M_{d30} temperature-map and $\Delta G^{\gamma \rightarrow \alpha}$ map of the area of secondary cracks, plus the related distribution of the calculated values.

which illustrates the distribution of the calculated M_{d30} values, is depicted. The M_{d30} map shows that the secondary cracks stop in the temperature range below $-20\text{ }^{\circ}\text{C}$. The regions in a temperature range below $-20\text{ }^{\circ}\text{C}$ are in agreement with the segregation zones of a high Ni content in Fig. 2.

Fig. 3b illustrates the calculated $\Delta G^{\gamma \rightarrow \alpha}$ values. The associated histogram shows the considered values of the $\Delta G^{\gamma \rightarrow \alpha}$ and their distribution as a function of the calculated $\Delta G^{\gamma \rightarrow \alpha}$ values. The crack propagation is stopped in front of the region with a $\Delta G^{\gamma \rightarrow \alpha}$ value of more than $-2,500\text{ J/mol}$ (Fig. 3b). These areas correspond to the region of microsegregation bands with a Ni content of at least 8 mass % (Fig. 2).

4. Discussion

4.1 Global and Local Consideration of the Microstructure

The chemical analysis by OES exhibits a homogeneous distribution of the alloying elements. Based on the global constitution of the investigated alloy AISI 304L it is simple to deduce an assumption about the stability of the austenite by calculated values such as the M_{d30} temperature, $\Delta G^{\gamma \rightarrow \alpha}$ or stacking fault energy. However, by the consideration of the global constitution the local composition in regard to microsegregation is disregarded. Microsegregation are responsible for local differences in the alloy composition. Therefore, the characteristics can't be assumed to be constant. A local destabilization of austenite may increase the sensitivity to hydrogen environment embrittlement. Especially, when the less stable zones or bands are located in the edge region. The investigation of the influence of microsegregations in the context of hydrogen environment embrittlement was carried out by tensile test in hydrogen atmosphere.

Specimens after tensile tests in air atmosphere performed at $-50\text{ }^{\circ}\text{C}$ show a ductile fracture surface without any further surface defects [19]. AISI 304L

tensile test specimens after examination in hydrogen atmosphere at $-50\text{ }^{\circ}\text{C}$ show a brittle fracture surface [19]. This fact was also observed in tensile tests of the steel grade AISI type 304 at $25\text{ }^{\circ}\text{C}$ in hydrogen atmosphere [6]. Beside the brittle failure of tensile test specimens, a typical feature of hydrogen environment embrittlement is the initiation and propagation of secondary cracks in the surface area [6]. Secondary cracks occur over the entire surface, mostly perpendicular to the stress direction (Fig. 1).

An investigation of the crack environment in terms of the local microstructure is necessary in order to obtain relevant information about the crack propagation. In this context, EDS measurement by means of line scan (one-dimensional) and mapping (two-dimensional) is a suitable method of analysis.

EDS analysis of the crack environment indicates that on the one hand microsegregations are present (Figs. 1a and 2) and on the other hand segregation bands with a high Ni content are responsible for the crack stop in Fig. 2. Focused on the concentration of the main elements Cr and Ni, Fig. 1a indicates that a local Ni content of 8.5 mass% and a local Cr content of 19 mass% (LS1) or 18 mass% (LS2) impede the crack propagation. This correlation suggests to calculate and compare the Cr and Ni equivalent in the region of the crack tip. The Cr and Ni equivalents was calculated according to the suggested equation of Schaeffler & Delong (Eq. (4), content in mass%) [25].

$$Gr_{eq} = Cr + 1.4Mo + 1.5Si + 0.5Nb + 2Ti$$

$$Ni_{eq} = Ni + 30(C + N) + 0.5Mn \quad (4)$$

The calculated results of the Cr and Ni equivalents, using the local chemical composition near the crack tip, are $Cr_{eq} = 20.4/Ni_{eq} = 12.1$ for LS1 and $Cr_{eq} = 19.1/Ni_{eq} = 12.3$ for LS2. The Cr and Ni equivalents of LS1 and LS2 near the crack tip are in the two-phase area of austenite + ferrite ($A + F < 10\%$), adjacent to the single-phase austenite. That result indicates a stable composition against martensite transformation in respect of the local

chemical composition. Stress assist formation of α' -martensite in austenitic steels is related to the susceptibility to hydrogen embrittlement [26-28]. Consequently, a high stability of austenite is necessary to obtain a high resistance against hydrogen embrittlement.

In this study two methods were used to calculate the local stability of austenite. Firstly, an empirical equation in order to calculate the M_{d30} temperature (Eq. 3). The lower the M_{d30} temperature the more stable is the austenitic phase. Secondly, the calculation of the chemical driving force for the $\gamma \rightarrow \alpha$ transformation ($\Delta G^{\gamma \rightarrow \alpha}$ -energy, Eq. (2)) by using Thermo-Calc database was performed. The latter method is based on the investigations of Borgenstam & Hillert [29] and Chatterjee *et al.* [30]. The more positive the value of $\Delta G^{\gamma \rightarrow \alpha}$ the more stable is the austenite. An estimation of the local stability of austenite by $\Delta G^{\gamma \rightarrow \alpha}$ is beneficial since all alloying elements and the temperature are considered.

In respect of the M_{d30} temperature and $\Delta G^{\gamma \rightarrow \alpha}$ the results indicate that local areas within the microstructure hinder or stop the crack propagation, dependent on a threshold value. As shown in Fig. 1b) the crack path passes through an area with a M_{d30} temperature above 0 °C and below a $\Delta G^{\gamma \rightarrow \alpha}$ of -2500 J/mol. In this region the stability of austenite is low. The crack propagation stops in regions with a M_{d30} temperature below -25 °C and a $\Delta G^{\gamma \rightarrow \alpha}$ above -2500 J/mol. By comparison, these values correspond to the calculated M_{d30} temperature and $\Delta G^{\gamma \rightarrow \alpha}$ value of the global composition of AISI 304L (Table 1). According to the global constitution of AISI 304L the calculated M_{d30} temperature and the $\Delta G^{\gamma \rightarrow \alpha}$ in Table 1 one might deduce a suitable resistance against hydrogen embrittlement. In contrary, AISI 304 grades are susceptible to hydrogen embrittlement in high pressure hydrogen atmosphere [3].

The chemical composition is an important determining factor to estimate the stability of austenite, however, an additional parameter which

affects the susceptibility of austenitic steels against hydrogen embrittlement is the grain size. According to literature, a grain size lower than approximately 6 μm reduces significantly the susceptibility of austenitic steels against hydrogen embrittlement by only slightly decrease of the ductility [31, 32]. In this context, a low grain size stabilizes the austenitic phase. For instance, a grain size lower than 22.5 μm (ASTM E 123 grain size number larger than 8) shifts the M_{d30} temperature to a lower temperature (Eq. (3)).

In relation to a small grain size, the existing studies detected that a grain size less than 5 μm leads to a significant increase of the SFE [8, 33, 34]. Moreover, the SFE is related to the formation of α' -martensite in austenitic steels. The deformation mechanism during plasticity is determined by the SFE [23]. As mentioned, a high SFE (approx. $\text{SFE} > 35 \text{ mJ/m}^2$) is related to the deformation mechanism of dislocation glide, whereas a low SFE (approx. $\text{SFE} < 12 \text{ mJ/m}^2$) is responsible for the martensite transformation by TRIP (TRansformation Induced Plasticity). This fact suggests to examine the crack environment by calculation of the local SFE. For this purpose, EDS data of line scans were used to calculate the local SFE by means of Eq. (1). The interfacial energy $\sigma^{\gamma/\epsilon}$ in Eq. (1) was recalculated from the measured SFE given in a work of Talonen *et al.* [35]. In addition, the recalculated interfacial energy of 22 mJ/m^2 was assumed to be constant. As shown in Fig. 1c, the scatter of the local calculated SFE is high along the analyzed path. According to that, it is impossible to assign a precise SFE value to the undamaged area in front of the crack tip. The results indicate that the cracks stop in the SFE range of 12 to 18 mJ/m^2 . These values correspond to the SFE of ϵ -martensite formation. In contrast to α' -martensite, ϵ -martensite exerts no detrimental influence in terms of hydrogen embrittlement [12, 13]. In contrast to the calculation of the SFE, more precise results in respect to the local stability of austenite were achieved by calculating the M_{d30} temperature and the value of $\Delta G^{\gamma \rightarrow \alpha}$ (Fig. 1).

Consequently, the evaluation of a two-dimensional data matrix, measured by means of EDS mapping (Fig. 2), was performed without consideration of the local SFE.

Up to now, this work dealt in detail with the investigation of EDS line scans near the crack path of damage and undamaged regions. A more precise study of the crack stop in front of microsegregation bands with a high stability of austenite makes it necessary to investigate the entire environment of secondary cracks. For this reason, the previously examined cracks were also investigated by EDS mapping (Fig. 2). The crack initiation takes place at the surface. In this matrix area the Ni content is below 8 mass%. Both cracks stop inside a microsegregation band with a Ni content above 8 mass%. Ni is a strong austenite former. Consequently, the local Ni content obviously affects the crack propagation. An increasing local stability of austenite inhibits the crack propagation (Fig. 3). In accordance to the calculations of the M_{d30} temperature and $\Delta G^{\gamma \rightarrow \alpha}$, the maximum stability of austenite occurs inside the microsegregation band of Ni. Therein, the M_{d30} temperature is about $-100\text{ }^{\circ}\text{C}$ and $\Delta G^{\gamma \rightarrow \alpha}$ is more positive than $-2,500\text{ mJ/m}^2$. Both histograms in Fig. 3 show the distribution of the M_{d30} temperature and $\Delta G^{\gamma \rightarrow \alpha}$. According to that, the average value of M_{d30} temperature is about $-25\text{ }^{\circ}\text{C}$ and the mean value of $\Delta G^{\gamma \rightarrow \alpha}$ is about $-2,600\text{ mJ/m}^2$. Related to the results of EDS line scans in terms of the local stability of austenite (Fig. 1b) a stop of crack propagation by a more positive $\Delta G^{\gamma \rightarrow \alpha}$ value ($\Delta G^{\gamma \rightarrow \alpha} > -2,500\text{ mJ/m}^2$) can be deduced.

Based on the results of this work, it was established that a global consideration of the chemical composition is not sufficient to describe adequately the susceptibility of austenitic stainless steels against hydrogen environment embrittlement. It was demonstrated that local microsegregation bands with a high stability of austenite are able to stop the propagation of secondary cracks. This feature enables by means of an adjusted manufacturing route to

produce conventional alloys with an increased resistance to hydrogen environment embrittlement.

5. Conclusions

In this work an austenitic stainless steel of the type AISI 304L was investigated by means of tensile test specimen which were tested in hydrogen atmosphere at 40 MPa pressure and at a temperature of $-50\text{ }^{\circ}\text{C}$. Main focus of this study was the investigation of the microstructure, considering microsegregations of all substitutional alloying elements with a content above 0.1 mass%, along or in the immediate environment of secondary cracks formed by hydrogen environment embrittlement. The local stability of austenite was calculated by using EDS data of substitutional elements and consideration of the interstitials C and N as constant values. EDS data were measured by line scans and mapping. The calculations were performed with an empirical equation (M_{d30} temperature) and by using a Thermo-Calc approach. The latter method was used, firstly, to calculate the difference in Gibbs free energy between the fcc- and bcc-phase ($\Delta G^{\gamma \rightarrow \alpha}$), secondly, to calculate the local stacking fault energy (SFE). The Thermo-Calc approach possesses the advantage of considering the influence of all alloying elements as well as the influence of the temperature. Assuming a homogeneous distribution of the elements C and N, the calculations with respect to the austenite stability were carried out. It was found that the crack propagation is stopped by a high local stability of austenite, in form of a Ni segregation band.

Acknowledgements

The authors gratefully acknowledge the financial support of the Deutsche Forschungsgemeinschaft within the project “Einfluss der lokalen chemischen Zusammensetzung auf die mikrostrukturelle Stabilität und lokale Verformungsmechanismen in Relation zur Wasserstoffversprödung von fcc Legierungen auf Fe-Basis” (DFG-Project No.: WE 4436/4-1).

References

- [1] Wang, C. and Nehrir, M. H. 2008. "Power Management of a Stand-Alone Wind/Photovoltaic/Fuel Cell Energy System." *IEEE Transactions on Energy Conversion* 23 (3): 957-67.
- [2] Shakya, B. D., Aye, L. and Musgrave, P. 2005. "Technical Feasibility and Financial Analysis of Hybrid Wind-Photovoltaic System with Hydrogen Storage for Cooma." *International Journal of Hydrogen Energy* 30 (1): 9-20.
- [3] Michler, T., Yukhimchuk, A. A. and Naumann, J. 2008. "Hydrogen Embrittlement Testing at Low Temperatures and High Pressures." *Corrosion Science* 50 (12): 3519-26.
- [4] Weber, S., Martin, M. and Theisen, W. 2011. "A Lean-Alloyed Austenitic Stainless Steel with High Resistance Against Hydrogen Environment Embrittlement." *Materials Science and Engineering: A* 528 (25-26): 7688-95.
- [5] Omura, T., Nakamura, J., Hirata, H., Jotoku, K., Ueyama, M. and Osuki, T. *et al.* 2016. "Effect of Surface Hydrogen Concentration on Hydrogen Embrittlement Properties of Stainless Steels and Ni Based Alloys." *ISIJ International* 56 (3): 405-12.
- [6] Martin, M., Weber, S., Izawa, C., Wagner, S., Pundt, A. and Theisen, W. 2011. "Influence of Machining-Induced Martensite on Hydrogen-Assisted Fracture of AISI Type 304 Austenitic Stainless Steel." *International Journal of Hydrogen Energy* 36 (17): 11195-206.
- [7] Gray, H. R. 1974. "Hydrogen Embrittlement Testing." ASTM 543 Spec. Techn. Publ., 34-47.
- [8] Singh, S. and Altstetter, C. 1982. "Effects of Hydrogen Concentration on Slow Crack-Growth in Stainless-Steels." *Metallurgical Transactions A* 13 (10): 1799-808.
- [9] Perng, T. P. and Altstetter, C. J. 1987. "Comparison of Hydrogen Gas Embrittlement of Austenitic and Ferritic Stainless-Steels." *Metallurgical and Materials Transactions A* 18 (1): 123-34.
- [10] Zhang, L., Wen, M., Imade, M. and Yokogawa, K. 2008. "Effect of Nickel Equivalent on Hydrogen Gas Embrittlement of Austenitic Stainless Steels Based on Type 316 at Low Temperatures." *Acta Materialia* 56 (14): 3414-21.
- [11] Schumann, H. 1975. "Verformungsinduzierte Martensitbildung in Metastabilen Austenitischen Stählen." *Kristall und Technik* 10 (4): 355-460.
- [12] Teus, S. M., Shvanyuk, V. N. and Gavriljuk, V. G. 2008. "Hydrogen-Induced $\gamma \rightarrow \epsilon$ Transformation and the Role of ϵ -Martensite in Hydrogen Embrittlement of Austenitic Steels." *Materials Science and Engineering: A* 497 (1-2): 290-4.
- [13] Shvanyuk, V. N., Foct, J. and Gavriljuk, V. G. 2003. "On a Role of Hydrogen-Induced ϵ -Martensite in Embrittlement of Stable Austenitic Steel." *Scripta Materialia* 49 (6): 601-6.
- [14] Mújica Roncery, L., Weber, S. and Theisen, W. 2010. "Development of Mn-Cr-(C-N) Corrosion Resistant Twinning Induced Plasticity Steels: Thermodynamic and Diffusion Calculations, Production, and Characterization." *Metallurgical and Materials Transactions A* 41 (10): 2471-9.
- [15] Mujica, L., Weber, S. and Theisen, W. 2012. "The Stacking Fault Energy and its Dependence on the Interstitial Content in Various Austenitic Steels." *Materials Science Forum* (706-709): 2193-8.
- [16] Nakano, J. and Jacques, P. J. 2010. "Effects of the Thermodynamic Parameters of the HCP Phase on the Stacking Fault Energy Calculations in the Fe-Mn and Fe-Mn-C Systems." *Calphad* 34 (2): 167-75.
- [17] Saeed-Akbari, A., Imlau, J., Prahl, U. and Bleck, W. 2009. "Derivation and Variation in Composition-Dependent Stacking Fault Energy Maps Based on Subregular Solution Model in High-Manganese Steels." *Metallurgical and Materials Transactions A* 40 (13): 3076-90.
- [18] Man, J., Kuběna, I., Smaga, M., Man, O., Järvenpää, A. and Weidner, A. *et al.* 2016. "Microstructural Changes during Deformation of AISI 300 Grade Austenitic Stainless Steels: Impact of Chemical Heterogeneity." In *Proceeding of 21st European Conference on Fracture*.
- [19] Martin, M. 2012. "Development of Lean Alloyed Austenitic Stainless Steels with a High Resistance to Hydrogen Environment Embrittlement." Ph.D. thesis, Ruhr University Bochum.
- [20] Fukuyama, S., Sun, D., Zhang, L., Wen, M. and Yokogawa, K. "Effect of Temperature on Hydrogen Environment Embrittlement of Type 316 Series Austenitic Stainless Steels at Low Temperatures." National Institute of Advanced Industrial Science and Technology (AIST), Kure 737-0197, Japan.
- [21] Olsen, G. B. and Cohen, M. A. 1976. "General Mechanism of Martensitic Nucleation: Part I. General Concepts and the FCC $\rightarrow$ HCP Transformation." *Metallurgical Transactions A* 7 (12): 1897-904.
- [22] Nohara, K., Ono, Y. and Ohashi, N. 1977. "Composition and Grain Size Dependencies of Strain-induced Martensitic Transformation in Metastable Austenitic Stainless Steels." *J. Iron and Steel Inst. Jpn* 63: 212-22.
- [23] Allain, S., Chateau, J.-P., Bouaziz, O., Migot, S. and Guelton, N. 2004. "Correlations between the Calculated Stacking Fault Energy and the Plasticity Mechanisms in Fe-Mn-C Alloys." *Materials Science and Engineering: A* 387-389: 158-62.
- [24] Dumay, A., Chateau, J.-P., Allain, S., Migot, S. and

- Bouaziz, O. 2008. "Influence of Addition Elements on the Stacking-Fault Energy and Mechanical Properties of an Austenitic Fe-Mn-C Steel." *Materials Science and Engineering: A* 483-484: 184-7.
- [25] Berns, H. and Theisen, W. 2008. *Eisenwerkstoffe: Stahl und Gusseisen*. 4th Edition, Springer.
- [26] Lai, C. L., Tsay, L. W. and Chen, C. 2013. "Effect of Microstructure on Hydrogen Embrittlement of Various Stainless Steels." *Materials Science and Engineering: A* 584: 14-20.
- [27] Michler, T., Berreth, K., Naumann, J. and Sattler, E. 2012. "Analysis of Martensitic Transformation in 304 Type Stainless Steels Tensile Tested in High Pressure Hydrogen Atmosphere by Means of XRD and Magnetic Induction." *International Journal of Hydrogen Energy* 37 (4): 3567-72.
- [28] Zhang, L., Li, Z., Zheng, J., Zhao, Y., Xu, P. and Zhou, C. *et al.* 2013. "Effect of Strain-Induced Martensite on Hydrogen Embrittlement of Austenitic Stainless Steels Investigated by Combined Tension and Hydrogen Release Methods." *International Journal of Hydrogen Energy* 38 (19): 8202-14.
- [29] Borgenstam, A. and Hillert, M. 1997. "The Driving Force for Lath and Plate Martensite and the Activation Energy for Isothermal Martensite in Ferrous." *Journal de Physique IV* 7 (5).
- [30] Chatterjee, S., Wang, H.-S., Yang, J. R. and Bhadeshia, H. K. D. H. 2006. "Mechanical Stabilisation of Austenite." *Materials Science and Technology* 22 (6): 641-4.
- [31] Macadre, A., Nakada, N., Tsuchiyama, T. and Takaki, S. 2015. "Critical Grain Size to Limit the Hydrogen-Induced Ductility Drop in a Metastable Austenitic Steel." *International Journal of Hydrogen Energy* 40: 10697-703.
- [32] Zan, N., Ding, H., Guo, X. F., Tang, Z. Y. and Bleck, W. 2015. "Effects of Grain Size on Hydrogen Embrittlement in a Fe-22Mn-0.6C TWIP Steel." *International Journal of Hydrogen Energy* 40: 10687-96.
- [33] Volosevich, P. Y., Grindnev, V. N. and Petrov, Y. N. 1976. "Manganese Influence on Stacking-Fault Energy in Iron-Manganese Alloys." *Physics of Metals and Metallography* 42: 126-30.
- [34] Lee, Y. K. and Choi, C. S. 2000. "Driving Force for $\gamma \rightarrow \epsilon$ Martensitic Transformation and Stacking Fault Energy of γ in Fe-Mn Binary System." *Metallurgical and Materials Transactions A* 31A: 355-60.
- [35] Talonen, J. and Hänninen, H. 2007. "Formation of Shear Bands and Strain-Induced Martensite during Plastic Deformation of Metastable Austenitic Stainless Steels." *Acta Materialia* 55 (18): 6108-18.