Synthesis and Characterization of PANI-MWCNTs Supported Nano Hybrid Electrocatalysts

Yuh-Jing Chiou¹, Meng-Yuan Chung¹, Hong-Ming Lin¹, Hsing-Yang Liu¹, Andrzej Borodzinski², Leszek Stobinski^{2,3}, Chung-Kwei Lin⁴ and Krzysztof Ryszard Kupiec²

1. Department of Chemical Engineering, Tatung University, Taipei 104, Taiwan

2. Institute of Physical Chemistry, Polish Academy of Sciences, Warsaw 02-507, Poland

3. Faculty of Materials Science and Engineering, Warsaw University of Technology, Warsaw 02-507, Poland

4. The School of Dental Technology, Taipei Medical University, Taipei 110, Taiwan

Abstract: Among new energy systems, fuel cells are electrochemical devices transforming chemical energy directly into electrical energy. In our previous works, MWCNTs (the multi walled carbon nanotubes) supported palladium anodic electrocatalysts for DFAFCs (direct formic acid fuel cells) have been studied. MWCNTs can be modified by appropriate oxides, for example, cerium oxide, zirconium oxide and N-doped titanium dioxide, to enhance the electrocatalytic performance of the catalysts. But the oxides and the defects of the acid oxidized MWCNTs, denoted as AO-MWCNTs, can cause the electron capture and reduce both the catalyst conductivity and the catalysts activity. In order to improve the conductive properties of the support, in the present work a conductive polymer was introduced to modify the surface of carbon nanotubes. PANI (polyaniline) has a long-chain structure and conjugated structure and exhibits good conductivity, high stability, and is non-toxic. After PANI modification, AO-MWCNTs can provide efficient electronic conduction network. In this study, PANI modified AO-MWCNTs were prepared via polymerization process. AO-MWCNTs were homogeneously coated with PANI to obtain composite with weight ratio 50:50 PANI to MWCNTs. The thickness of the PANI layer was 4-9 nm. It was shown that the photosynthesis process is a better method to reduce Pd on PANI/AO-MWCNTs than by using NaBH₄. By adjusting pH value to 9, during preparation of Pd/PANI/AO-MWCNTs composites by X-ray irradiation process, smaller Pd particles were obtained and PANI deprotonation was avoided which explains better activity of this composite in formic acid electro oxidation.

Key words: Polyaniline, palladium, DFAFCs, MWCNTs.

1. Introduction

The energy obtained from renewable fuels, such as hydrogen, methanol, ethanol and formic acid, which will not cause environmental pollution, is usually referred to as green energy. The fuels are used in fuel cells in which electricity is generated with energy efficiency up to 70% compared to 30-40% for combustion engines [1-5]. Nano hybrid materials play an important role in enhancing fuel cells efficiency. As the metal particle size decreases the surface area increases. In a fuel cell, the electrochemical reaction rate is usually proportional to the electrochemically

available surface area, so the activity increases with decreasing of the particle size. Manufacturing catalyst with nano size metal particles and high dispersion is a challenge for the application of nanotechnology in the fuel cells area.

In the electrocatalysis, carbon supported catalysts are commonly used. Carbon nanotubes became the most frequently used support since their discovery by Iijima in 1991 [6-10]. Besides the nano size, they have many advantages such as large surface area, good heat conductivity and electronic conductivity and provide good access for the reactants [11-15]. That is the reason why carbon nanotubes found many applications, such as field emission display, hydrogen storage, nano probe, transistor, and nano clamp, etc.

Corresponding author: Hong-Ming Lin, professor, research fields: synthesis of nanomaterials, formic acid fuel cells, nanowires, gas sensors.

[16-20]. Recently carbon nanotubes have been employed in biotechnology and energy conversion including the application in fuel cell catalysts [21-24].

In our labs, we studied a series of Pt and Pd catalysts supported on MWCNTs (the multi walled carbon nanotubes) for DMFCs (direct methanol fuel cells) and DFAFCs (direct formic acid fuel cells). Some metal oxides modification of MWCNTs can enhance the electrocatalytical performance. The series of studies include Pt/CeO₂/MWCNTs [25], Pt/NiO/MWCNTs [26], Pd/CeO₂/MWCNTs [27], and Pd/ZrO₂/MWCNTs [28, 29]. Addition of the second metal (Au) to Pd, to form Au-Pd solid solution, can also increase the catalyst activity of the formic acid electro oxidation and prevent Pd leaching in acid solution [30].

Recently, various conducting polymers have been used as a support of electrocatalysts [31, 32]. One of them is PANI (polyaniline), which has three main distinguishable oxidation states, namely, the fully reduced (leucoemeraldine), the half oxidized (emeraldine), and the fully oxidized (pernigraniline) state, with virtually an infinite number of possible oxidation states existing in between. Protonation of the polymer, also known as doping, is the mechanism by which polyaniline becomes electrically conductive [33]. The classical chemical synthesis involves the direct oxidation of aniline monomers by chemical oxidants. It can be synthesized by anodic oxidation of aniline monomers on an inert electrode. Recently, some researchers developed X-ray synthesis to obtain PANI nanofibers [34].

In this study, the conductive polymer, PANI, has been used to modify the surface of MWCNTs to form a composite applied as a support of Pd catalysts for formic acid electro oxidation. The purpose of this work is to improve the electrical conductivity of the composites by forming a PANI-MWCNTs network with enhanced effective electron transfer, as illustrated in Fig. 1.

High pH environment during the deposition of

palladium can help the formation of small particle size. However, polyaniline deposition has to be carried out in acidic solution to maintain it high conductivity. Pd/PANI/MWCNTs composites were prepared in wide pH range to find the optimal condition. Their structures, compositions and electrocatalytical performance were studied.

2. Experimental

Multi-walled carbon nanotubes (Yong-Zhen Technomaterial CO., LTD, China) of purity 98%~99% were first refluxed in nitric acid (Merck, 65%) for 9 hours to remove the impurities and to introduce functional groups improving hydrophilicity. The acid treated MWCNTs were then filtered, washed by deionized water (Mili-Q system, resistivity 18.2 MΩcm), and dried in a vacuum oven at 100 °C. 0.2 g of the AO-MWCNTs was dispersed in 20 mL toluene. 0.1285 g of ammonium persulfate was dissolved in 20 mL 1 M sulfuric acid. The two solutions were then mixed and 0.2 mL of aniline was added to react at 4 °C for 4 hours with vigorous stirring. The prepared

Fig. 1 The illustration of PANI modification helps (a) network forming with MWCNTs and (b) electron transferring during electrocatalysis.

PANI/AO-MWCNTs with weight ratio of 50:50 were obtained by filtering and washing with diluted sulfuric acid.

Pd/PANI/AO-MWCNTs were prepared by the two methods described below. In order not to destroy PANI, further heat treatment was not applied.

2.1 Reduction by NaBH_4

50 mg of the prepared supports, AO-MWCNTs or PANI/AO-MWCNTs were dispersed in 50 mL of DI water. After mixing with stoichiometric amount of PdCl_2 , 0.1 M NaBH_4 was added dropwise, and reaction was continued for 2 hours with stirring. The product, denoted as Pd/PANI/AO-MWCNTs- NaBH_4 , was obtained by filtering, washing by DI water and dried.

2.2 X-Ray Photosynthesis

PANI/AO-MWCNTs and PdCl_2 precursor solution were mixed in 15 mL of DI water and Pd was deposited using photo-reduction method, in Taiwan National Synchrotron Radiation Center in Hsinchu, Taiwan, by subjecting the sample to hard X-ray radiation for 30 minutes with rigorous stirring. The products were obtained by centrifuging and washing with DI water to remove Cl^- , and dried. The mechanism of X-ray synthesis to prepare palladium hybrid catalysts is illustrated in Fig. 2a. By irradiating water, a number of strong reducers, including $\text{H}^\bullet$, e_{aq}^- and H_2 , are generated, and metal precursor is reduced rapidly [35]. The scheme of the photosynthesis process is shown in Fig. 2b.

XRD (X-Ray Diffraction), SEM (Scanning Electron Microscopy), and ICP-OES (Inductively Coupled Plasma Optical Emission Spectroscopy) (Perkin Elmer Optima-2000 DV) were used to characterize the structure, composition, and morphology of the hybrid nanoparticles. The electrochemical performance of the Pd based catalysts was tested by CV method in a three-electrode system using CHI Model 6081C potentiostat/galvanostat instrument. The catalyst ink for the working electrode is composed of 5 mg of

catalyst, 0.05 mL, 5% Nafion solution (DuPont Fluoroprodut, DE-2021), 5 mg carbon black (Vulcan XC-72), and 5 mL ethanol. The well mixed ink is dropped onto a glassy carbon disc (Toyo Tanso, IG-45, $9.0 \mu\Omega\text{m}$) and dried in 85°C . The prepared working electrode had Pd loading about 0.1 mg/cm^2 which was exactly determined by ICP-OES. In the experiment, Ag/AgCl was used as the reference electrode, and a Pt grid was the counter electrode. A mixture of 3 M formic acid and 1 M sulfuric acid was used as the electrolyte. The scan range was -0.2 to 1.0 V and the scan rate 10 mV/sec. The measured current was then normalized by the measured Pd weight.

3. Results and Discussion

The SEM morphologies of the synthesized PANI/AO-MWCNTs with various ratios are shown in Figs. 3a-3c. In Fig. 3a, the acid treated MWCNTs have the average diameter of 23 nm and more than 1 μm length. In Fig. 3b, PANI/AO-MWCNTs 80:20, with more PANI, have more film-like structure. For PANI/AO-MWCNTs 50:50 in Fig. 3c, AO-MWCNTs are homogeneously covered by PANI with less film like structure. The diameter of PANI modified

Mechanism of Photosynthesis:

(a)

Fig. 2 (a) The photosynthesis mechanism and (b) the experimental setup of the photosynthesis process.

Fig. 3 SEM morphologies of (a) AO-MWCNTs, (b) PANI/AO-MWCNTs 80:20, (c) PANI/AO-MWCNTs 50:50, (d) FTIR spectra of the commercial PANI, AO-MWCNTs and PANI/AO-MWCNTs 50:50, CV plots of (e) Pd/PANI/AO-MWCNT obtained by NaBH₄ reduction, and (f) SEM morphology of Pd/PANI/MWCNT-NaBH₄.

AO-MWCNTs increases to 30-40 nm, then is homogeneously covered by PANI with less film like structure. The diameter of PANI modified AO-MWCNTs increases to 30-40 nm. Then the thickness of the PANI film coated on AO-MWCNTs can be evaluated to be 4-9 nm. The FTIR (Fourier Transform Infrared) spectra in Fig. 3d show the characteristic peaks of PANI stretching mode; C-N stretching is found at 1,000-1,350 cm⁻¹. At the range of 500 to 800 cm⁻¹, the peaks can be assigned to the PANI 1, 4-ring and 1, 2-ring substitutions and may be smoothed as a result of PANI interaction with AO-MWCNTs [34].

Because PANI/AO-MWCNTs 50:50 have better morphology which is similar to our original illustration in Fig. 1a, Pd was then deposited onto PANI/AO-MWCNTs 50:50 via different methods and denoted as Pd/PANI/ AO-MWCNTs. The presence of deposited Pd on the hybrid supports has been confirmed by XRD.

The CV result of the Pd/PANI/AO-MWCNTs via reduction by NaBH₄ is shown in Fig. 3e. The maximum current at 0.5 V is assigned as the oxidation

current of formic acid catalyzed by Pd. The currents for potentials in the range between 0.1 V to 0.9 V with maximum at 0.5 V are assigned to the oxidation current of formic acid catalyzed by Pd. For Pd/PANI/AO-MWCNT-NaBH₄, the current density is less than 30 mA/mg Pd after 20 CV cycles. The Pd synthesized by NaBH₄ reduction is well dispersed on the support with particle size of 5-10 nm as shown in Fig. 3f. The Pd size of Pd/PANI/AO-MWCNT-NaBH₄ is quite similar to that in our previous studies [25-30]. The observed decay in current density of formic acid oxidation, during subsequent CV cycles, may be caused by Pd dissolution at high potentials. The other possibility is that the Pd can be contaminated by impurities contained in the composite. On the basis of our previous results [25-30], it may be suggested that this deactivation is caused by impurities presented on the samples after catalysts preparation. In this study, one of such impurities may be aniline adsorbed on the support during polymerization, and then it may spill over to the surface of Pd particles during the electrochemical tests. A proper heat treatment under

Fig. 4 SEM morphologies of Pd/PANI/AO-MWCNTs via photosynthesized in different pH values: (a) pH 1, (b) pH 2, (c) pH 3, (d) pH 4, (e) pH 5, (f) pH 6, (g) pH 7, (h) pH 8, (i) pH 9, (j) pH 10, (k) pH 11, and (l) pH 12.

5% H_2/Ar 200 °C could improve the catalyst performance by removing of impurities adsorbed on the surface of Pd, but unfortunately this high temperature treatment increases Pd particle size and may cause the reduction or decomposition of PANI, so heat treatment is not employed in the study.

X-ray photosynthesis method is introduced in this study to reduce Pd during several minutes at room temperature. In order to optimize the acid-basic condition of X-ray photosynthesis, pH values were

adjusted to different values in the range 1-12 to obtain the Pd catalysts. The morphologies of the composites obtained at different pH values are shown in Figs. 4a-4l. For low pH values, Pd particles are quite large and aggregate, with most particles larger than 50 nm for pH 2-7. In alkaline pH conditions, pH 8-12, Pd is dispersed well on the support and Pd particles have smaller sizes. The average particle size and the range are listed in Table 1. In different pH values, the photosynthesized Pd/PANI/AO-MWCNTs have 11-20

wt.% Pd as determined by ICP-OES. In low pH preparation conditions, it is difficult to deposit Pd on surface of PANI modified MWCNTs. But in alkaline conditions, the amount of Pd deposited is close to the nominal value designed as 20 wt.%.

The last two rows in Table 1 show the CV results: the maximum current density of the 20th cycle and the corresponding potential of Pd/PANI/AO-MWCNTs in photosynthesis in pH 1 to 12. The peak associated to the Pd catalyzed formic acid oxidation is often at 0.3~0.6 V. In Table 1, it's observed that the Pd/PANI/AO-MWCNTs synthesized in alkaline conditions show the better activity of formic acid electro oxidation because the Pd particles are smaller. The high current density (131 mA/mg) for the sample

synthesized at pH = 1 could be caused by higher conductivity of PANI obtained under these conditions. The better electro catalytic performance of the Pd particle produced at high pH preparing conditions is consistent with their smaller particle sizes. Pd/PANI/AO-MWCNTs photosynthesized at pH value 9 have small Pd particle size and simultaneously deprotonation of PANI is not observed, which explains the best electrocatalytic performance of this composite.

Fig. 5 shows the electrochemical impedance spectroscopy of the Pd catalysts prepared in different pH conditions. The plot can show the resistance of the material in a specific electrochemical condition. At pH 2 during synthesis, the hybrid catalysts have resistance

Table 1 Pd composition, the maximum current density of the 20th cycle, and the corresponding potential of Pd/PANI/AO-MWCNTs photosynthesized in pH 1-12.

pH	1	2	3	4	5	6	7	8	9	10	11	12
Pd size nm*	23	26	NA**	55	28	32	23	3	3	3	3	4
Range nm	10-50	20-100	15-100	50-80	20-50	8-40	5-30	2-5	3-5	2-8	2-5	2-10
Pd wt. %	12.0	12.9	13.7	12.8	11.0	17.6	11.6	16.3	14.3	14.9	17.4	20.6
Peak current, mA/mg Pd	131	10	28	28	15	85	33	222	414	176	189	309
Peak potential, mV	0.3	0.1	0.1	0.1	0.1	0.3	0.1	0.5	0.6	0.3	0.4	0.6

* Pd particle size is obtained from the SEM images in Fig. 4.

** In pH 3, the particles aggregate seriously and the average size cannot be evaluated.

Fig. 5 Impedance of Pd/PANI/MWCNTs photosynthesized in different pH values. Reference electrode: Ag/AgCl, counter electrode: Pt, electrolyte: 3 M formic acid and 1 M sulfuric acid.

about $4 \Omega\text{cm}^2$, and the resistance increases to $7 \Omega\text{cm}^2$ in basic pH 12. The low pH adjustment during photosynthesis improves the conductivity of Pd/PANI/AO-MWCNTs. But the difference is not very large.

Because Pd/PANI/AO-MWCNTs photosynthesized in high pH values perform better in formic acid electrooxidation, it may be concluded that positive effect of decreasing of Pd particles sizes dominates over the negative effect of decreasing of PANI conductivity.

4. Conclusions

PANI modified AO-MWCNTs composites have been prepared successfully by chemical procedure. In the case of PANI/AO-MWCNTs composite with weight ratio 50:50, PANI is deposited homogeneously with thickness 4-9 nm on the surface of acid treated MWCNTs. The coating improved conductivity of AO-MWCNTs by electrical bridging modification of the defects caused by their nitric acid pretreatment. NaBH_4 used to reduction of Pd precursor may partly decrease PANI conductivity. The photosynthesis process is a better method to produce Pd/PANI/AO-MWCNTs. By adjusting pH to 9, during preparation of Pd/PANI/AO-MWCNTs, small Pd particles are formed and PANI is not deprotonated, which explains its high activity in formic acid electro oxidation. During the formic acid electro oxidation, electrons can pass easier through the surface of conductive polymer coated AO-MWCNTs and are not being trapped by defects of AO-MWCNTs. Using X-ray irradiation and applying proper pH conditions it was possible to produce Pd-based catalysts on PANI modified AO-MWCNTs as innovated novel electrocatalysts for DFAFCs.

Acknowledgments

The authors deeply acknowledge the grant of the Ministry of Science and Technology of Taiwan (NSC 103-2923-E-036-001-MY3) and the Polish National

Centre for Research and Development (DKO/PL-TW1/1/2013) for financial support of this research.

References

- [1] Iijima, S. 1991. "Helical Microtubules of Graphitic Carbon." *Nature* 354: 56-8.
- [2] Peigney, A., Laurent, C., Flahaut, E., and Rousset, A. 2000. "Carbon Nanotubes in Novel Ceramic Matrix Nano Composites." *Ceramics International* 26: 677-83.
- [3] Kim, J. M., Choi, W. B., Lee, N. S., and Jung, J. E. 2000. "Field Emission from Carbon Nanotubes for Displays." *Diamond and Related Materials* 9: 1184-9.
- [4] Kong, J., Chapline, M. G., and Dai, H. 2001. "Functionalized Carbon Nanotubes for Molecular Hydrogen Sensors." *Advanced Materials* 13: 1384-6.
- [5] Collins, P. G., Bradley, K., Ishigami, M., and Zettl, A. 2000. "Extreme Oxygen Sensitivity of Electronic Properties of Carbon Nanotubes." *Science* 287: 1801-4.
- [6] Zahab, A., Spina, L., Poncharal, P., and Marliere, C. 2000. "Water-Vapor Effect on the Electrical Conductivity of a Single-Walled Carbon Nanotube Mat." *Physical Review B* 62: 10000-3.
- [7] Martel, R., Schmidt, T., Shea, H. R., Hertel, T., and Avouris, Ph. 1998. "Single- and Multi-wall Carbon Nanotube Field-Effect Transistors." *Applied Physics Letters* 73: 2447-9.
- [8] Soh, H. T., Quate, C. F., Morpurgo, A. F., Marcus, C. M., Kong, J., and Dai, H. 1999. "Integrated Nanotube Circuits: Controlled Growth and Ohmic Contacting of Single-Walled Carbon Nanotubes." *Applied Physics Letters* 75: 627-9.
- [9] Kong, J., Franklin, N. R., Zhou, C., Chapline, M. G., Peng, S., Cho, K., and Dai, H. 2000. "Nanotube Molecular Wires as Chemical Sensors." *Science* 287: 622-5.
- [10] Chen, R. J., Franklin, N. R., Kong, J., Cao, J., Tombler, T. W., Zhang, Y., and Dai, H. 2001. "Molecular Photodesorption from Single-Walled Carbon Nanotubes." *Applied Physics Letters* 79: 2258-60.
- [11] Varghese, O. K., Kichambre, P. D., Gong, D., Ong, K. G., Dickey, E. C., and Grimes, C. A. 2001. "Gas Sensing Characteristics of Multi-wall Carbon Nanotubes." *Sensors and Actuators B* 81: 32-41.
- [12] Ong, K. G., Zeng, K., and Grimes, C. A. 2002. "A Wireless, Passive Carbon Nanotube-Based Gas Sensor." *IEEE Sensor Journal* 2: 82-8.
- [13] Chopra, S., Pham, A., Gaillard, J., Parker, A., and Rao, A. M. 2002. "Carbon-Nanotube-Based Resonant-Circuit Sensor for Ammonia." *Applied Physics Letters* 80: 4632-4.

- [14] Ong, K. G., and Grimes, C. A. 2000. "A Resonant Printed-Circuit Sensor for Remote Query Monitoring of Environmental Parameters." *Smart Materials and Structures* 9: 421-8.
- [15] Dai, H. 2002. "Carbon Nanotubes: Opportunities and Challenges." *Surface Science* 500: 218-41.
- [16] Dai, H., Hafner, J. H., Rinzler, A. G., Colbert, D. T., and Smalley, R. E. 1996. "Nanotubes as Nanoprobes in Scanning Probe Microscopy." *Nature* 384: 147-50.
- [17] Wong, S. S., Joselevich, E., Woolley, A. T., Cheung, C. L., and Lieber, C. M. 1998. "Covalently Functionalized Nanotubes as Nanometre-sized Probes in Chemistry and Biology." *Nature* 394: 52-5.
- [18] De Heer, W. A., Chatelain, A., and Ugarte, D. 1995. "A Carbon Nanotube Field-Emission Electron Source." *Science* 270: 1179-80.
- [19] Tans, S. J., Verschueren, A. R., and Dekker, C. 1998. "Room-Temperature Transistor Based on a Single Carbon Nanotube." *Nature* 393: 49-52.
- [20] Wang, C., Waje, M., Wang, X., Tang, J. M., Haddon, R. C., and Yan, Y. 2004. "Proton Exchange Membrane Fuel Cells with Carbon Nanotube Based Electrodes." *Nano Letters* 4: 345-8.
- [21] Matsumoto, T., Komatsu, T., Arai, K., Yamazaki, T., Kijima, K., Shimizu, H., Takasawa, Y., and Nakamura, J. 2004. "Reduction of Pt Usage in Fuel Cell Electrocatalysts with Carbon Nanotube Electrodes." *Chemical Communications*: 840-1.
- [22] Tang, H., Chen, J. H., Huang, Z. P., Wang, D. Z., Ren, Z. F., Nie, L. H., Kuang, Y. F., and Yao, S. Z. 2004. "High Dispersion and Electrocatalytic Properties of Platinum on Well-Aligned Carbon Nanotube Arrays." *Carbon* 42: 191-7.
- [23] Li, W., Liang, C., Qiu, J., Zhou, W., Han, H., Wei, Z., Sun, G., and Xin, Q. 2002. "Carbon Nanotubes as Support for Cathode Catalyst of a Direct Methanol Fuel Cell." *Carbon* 40: 791-4.
- [24] Li, W., Liang, C., Zhou, W., Qiu, J., Zhou, Z., Sun, G., and Xin, Q. 2003. "Preparation and Characterization of Multi-walled Carbon Nanotube-Supported Platinum for Cathode Catalysts of Direct Methanol Fuel Cells." *Journal of Physical Chemistry B* 107: 6292-9.
- [25] Chen, C. H., Chiou, Y. J., Liou, W. J., Lin, W. S., Lin, H. M., and Wu, S. H. 2011. "Synthesis and Electrocatalysis Application of Hybrid Platinum/Cerium Oxide/Multi-walled Carbon Nanotubes." *Functional Materials Letters* 4: 295-8.
- [26] Cheng, I. L., Chiou, Y. J., and Lin, H. M. 2012. "Synthesis and Characterization of Hybrid Pt/NiO/MWCNTs Electrocatalysts." *Journal of the Chinese Chemical Society* 59: 1345-50.
- [27] Shen, Y. C. 2014. "Synthesis and Characterization of Pd-based/CeO₂/MWCNTs Nanohybrid Electrocatalysts." Master thesis, Tatung University, Taiwan.
- [28] Hsu, Y. 2014. "Synthesis and Characterization of Nano Hybrid AuPd/ZrO₂/MWCNTs Electrocatalysts." Master thesis, Tatung University, Taiwan.
- [29] Malolepszy, A., Mazurkiewicz, M., Stobinski, L., Lesiak, B., Kövér, L., Tóth, J., Mierzwa, B., Borodzinski, A., Nitze, F., and Wagberg, T. 2015. "Deactivation Resistant Pd-ZrO₂ Supported on Multiwall Carbon Nanotubes Catalyst for Direct Formic Acid Fuel Cells." *International Journal of Hydrogen Energy* 40: 16724-33.
- [30] Chiou, Y. J., Chen, K. Y., Lin, H. M., Liou, W. J., Liou, H. W., Wu, S. H., Mikolajczuk, A., Mazurkiewicz, M., Malolepszy, A., Stobinski, L., Borodzinski, A., Kedzierzawski, P., Kurzydowski, K., Chien, S. H., and Chen, W. C. 2011. "Electrocatalytic Properties of Hybrid Palladium-gold/Multi-walled Carbon Nanotube Materials in Fuel Cell Applications." *Physical Status Solidi A* 208: 1778-2.
- [31] Antolini, E., and Gonzalez, E. R. 2009. "Polymer Supports for Low-Temperature Fuel Cell Catalysts." *Applied Catalysis A: General* 365: 1-19.
- [32] Malinauskas, A. 1999. "Electrocatalysis at Conducting Polymers." *Synthetic Metals*: 10775-83.
- [33] Song, E., and Choi, J. W. 2013. "Conducting Polyaniline Nanowire and Its Applications in Chemiresistive Sensing." *Nanomaterials* 3: 498-523.
- [34] Felix, J. F., Barros, R. A., de Azevedo, W. M., and da Silva Jr., E. F. 2011. "X-ray Irradiation: A Non-conventional Route for the Synthesis of Conducting Polymers." *Synthetic Metals* 161: 173-6.
- [35] Bae, H. B., Oh, S. H., Woo, J. C., and Choi, S. H. 2010. "Preparation of Pt-Ru@Polypyrrole-MWNT Catalysts by Irradiation and Chemical Reduction and Their Adsorption Capacity for CO." *Journal of Nanoscience and Nanotechnology* 10: 6901-6.