Substituent Effect of Chiraldiphenyl Salen Metal (M = Fe(II), Co(II), Ni(II), Cu(II), Zn(II)) Complexes for New Conceptual DSSC Dyes

Shun Yamane¹, Yuuki Hiyoshi¹, Shinnosuke Tanaka¹, Shun Ikenomoto¹, Takashi Numata¹, Kazuya Takakura¹, Tomoyuki Haraguchi¹, Mauricio A. Palafox², Michikazu Hara³, Mutsumi Sugiyama⁴ and Takashiro Akitsu¹

1. Department of Chemistry, Faculty of Science, Tokyo University of Science, 1-3 Kagurazaka, Shinjuku-ku, Tokyo 1628601, Japan

2. Departamento de Química-Física I, Facultad de Ciencias Químicas, Universidad Complutense de Madrid, Madrid 28040, Spain

3. Materials and Structures Laboratory, Tokyo Institute of Technology, Nagatsuta-cho 4259, Midori-ku, Yokohama-city, Kanagawa, 226 8503, Japan

4. Department of Electrical Engineering, Faculty of Science and Technology, Tokyo University of Science, 2641 Yamazaki, Noda, Chiba 278 8510, Japan

Abstract: The authors have designed and synthesized new chiral salen-type metal (M = Fe, Co, Ni, Cu, Zn) complexes (1-5) for new conceptual dyes (co-sensitizer or colorful multi-dyes) of DSSCs (dye-sensitized solar cells). The authors measured substituent effects on their absorption spectra and redox properties, and compared them with TD-DFT (time-dependent density functional theory) calculations. Electron withdrawing groups resulted in red-shift of ultraviolet-visible (UV-Vis) spectra. For the first time, the authors also proposed and confirmed the importance of substituent effects on their electric transition dipole moments, calculated by TD-DFT for designing dyes. Chemisorption for TiO₂ of the complex by carboxyl groups was confirmed by XPS measurement. In view of electronic properties, all compounds have the possibility to be dyes of DSSCs.

Key words: DSSCs (Dye-sensitized solar cells), salen complexes, chirality, DFT.

1. Introduction

Along with the growing awareness of fossil fuel depletion, sustainable energy, especially solar energy, has received attention in various research fields [1-8]. DSSCs (Dye-sensitized solar cells) have been improved by Grätzel [9] since 1991, and they have gradually been regarded as prospective energy sources due to their high design ability and low manufacturing cost compared with conventional silicon-based solar cells and thin-film photovoltaic technologies. Dyes of DSSC are mainly Ru complexes, and the efficiency of DSSC has been recorded as 11.4% (theoretically 30%) [10]. However, since the amount of Ru is sometimes limited and the problem of obtaining a stable supply

can exist, alternatives have been sought for years [11, 12]. High efficiency DSSC strongly demands dye to have absorbing wide light. For example, a typical N719 ([RuL₂(NCS)₂]:2TBA; L = 2,2'-bipyridyl-4,4'-dicarboxylic acid, TBA = tetra-n-butyl ammonium) dye is capable of photoelectric conversion until 900 nm [13]. N719 contains carboxyl groups and NCS⁻ ligands to adsorb on the TiO₂ surface via interaction with the Ti2p and O1s orbitals, and interactions of their S atoms, respectively [14]. However, NCS⁻ ligands are labile and susceptible to degrade through dissociation. Therefore, the authors do not use NCS⁻ to improve dye stability or control the adsorption structure, but use only carboxyl groups. Anti-bonding orbitals are formed by overlapping of O2p, C2p orbitals of carboxyl groups, and Ti3d orbitals when dyes are adsorbed on TiO₂. Absorption

Corresponding author: Takashiro Akitsu, Prof. Dr., main research field: inorganic coordination chemistry.

of the complex is then extended by changes of electronic states [15]. Analyzing the adsorption structure is critical to improving efficiency. However, details of the structure have not yet been elucidated [16, 17].

While the authors search valid ligands for DSSCs, the authors focus on salen-type metal complexes due to their following characteristics:

(1) Their synthesis and chemical modification are easier than what is required for existing dyes.

(2) They have higher stability than existing dyes due to the presence of chelating ligands.

Therefore, salen metal complexes have potential for use as new conceptual dyes (co-sensitizer or colorful multi-dyes) in DSSCs.

Increasing the PCE of Schiff base Zn(II) complexes by varying the substituents has been reported [18]. In addition, the UV-Vis spectra of salen Al(III), Ni(II), and Cu(II) complexes were found to be red-shifted following the incorporation of electron-withdrawing substituents [19, 20]. The chiral salen-type complexes showed a peak shift by the substituent effect of aldehyde moiety [21]. It is therefore expected that substituent effects in salen metal complexes should be useful for controlling absorption, as well as E^0 values.

In this study, the authors systematically compare characteristics of the complexes with different central metals (M = Fe(II), Co(II), Ni(II), Cu(II), and Zn(II)). The authors examined the adsorption state of the complex to the TiO_2 by XPS measurement. Detailed investigations of the performances of their DSSC devices were achieved in comparison with those of DSSC of N3. To examine the correlation between absorption wavelength and photoelectric conversion wavelength, we performed IPCE (incident photon-to-current efficiency) measurement.

2. Experimental

2.1 Materials and Methods

Potassium hydroxide, 3,5-dichlorosalicylaldehyde

were purchased from Wako (Japan). Manganese(II) acetate tetrahydrate was purchased from Sigma-Aldrich Co., Ltd. (U.S.A.). Iron sulfate(II) heptahydrate, cobalt(II) acetate tetrahydrate, nickel(II) acetate tetrahydrate, and Zn(II) acetate dihydrate were purchased from Kanto Chemical Co., Inc. (Japan). Salicylaldehyde, 5-bromosalicylaldehyde, 3,5-dibromosalicylaldehyde, and 5-chlorosalicylaldehyde were obtained from Tokyo Chemical Industry (Japan).

4,4'-((1*S*,2*S*)-1,2-diammonioethane-1,2-diyl)dibenzoate was prepared according to extant literature [22, 23].

Elemental analyses (C, H, and N) were performed using a Perkin-Elmer 2400 II CHNS/O analyzer at the Tokyo University of Science. IR spectra were recorded as KBr pellets on a JASCO FT-IR 4200 plus spectrophotometer in the range 4,000-400 cm^{-1} at 298 K. Absorption spectra were obtained on a JASCO V-570 UV-vis-NIR spectrophotometer in the range 1,500-200 nm at 298 K. CD spectra were obtained on a JASCO J-820 spectropolarimeter in the range 900-250 nm at 298 K. CV curves were obtained via BAS AIS/DY2323 using a traditional three-electrode system. The working, reference, and auxiliary electrodes were a Pt disk, Ag/Ag^+ and Pt wire, respectively. XPS was carried out using an Mg $K\alpha$ source SHIMADZU, ESCA 3400. The performance of DSSC was derived from current density-voltage (J - V) curves measured under air mass 1.5 conditions at an illumination of 100 mW/cm^2 by an ADCMT 6241A DC Voltage/Current Source/Monitor, and IPCE measured by Basic Monochromatic Light Irradiation System Model SM-25 in the range 800-270 nm. All measurements were performed at room temperature. Powder X-ray diffraction patterns of complexes were collected at 298 K with a Rigaku Smart Lab at the University of Tokyo.

2.2 Synthesis

The detailed synthesis methods are written for the supporting information. Most complexes had K as

-COOK in elemental analyses from dropwise potassium hydroxide.

2.3 Calculations

Calculations were performed using the Gaussian 09W software Revision D.01 [24]. Fe complexes calculations were performed using the Gaussian 09W software Revision C.01. Geometry optimizations in the gas phase and vertical excitation energies of Fe, Co, Ni-(1-5) were performed using TD-DFT with the CAM-B3LYP/6-31 + G(d). These of Cu, Zn-(1-5) were performed using TD-DFT with the B3LYP/6-31 + G(d). The calculation of excitation energies was based on ground-state geometry.

3. Results and Discussion

3.1 Synthesis

The ligand was synthesized by condensation of 4,4'-((1*S*,2*S*)-1,2-diaminoethane-1,2-diyl) dibenzoic acid in the presence of two equivalents of 3-Y,5-X-salicylaldehyde. Fe (Sal), Co (Sal), Ni (Sal),

and Cu (Sal) were synthesized by reacting H₂ (Sal) with the corresponding metal acetate salts (FeSO₄·7H₂O, Co(OAc)₂·4H₂O, Ni(OAc)₂·4H₂O and Cu(OAc)₂·4H₂O).

To adsorb these complexes onto semiconductor surfaces, it was functionalized with COOH anchoring groups to create complex M-(1-5) using the synthetic procedure described in the Methods. These complexes are presented in Fig. 1. The COOH groups of M-(1-5) were attached as 4,4'-((1*S*,2*S*)-1,2-diaminoethane-1,2-diyl) dibenzoic acid.

3.2 Rietveld Structural Analysis

Structural analysis for Cu-1, Cu-3, and Zn-2 by the Rietveld method [25] was carried out using PDXL2 ver. 2.2.1.0 (Rigaku Corporation).

3.3 Structure Description of Cu-1, Cu-3, and Zn-2

The complex Cu-1 crystalizes in monoclinic, space group *P*2₁ with *Z* = 2. As shown in Fig. 2, the

Fig. 1 Chiral salen complexes of 25 compounds (M = Fe, Co, Ni, Cu, Zn-(1-5)).

Compounds	X	Y
Fe, Co, Ni, Cu, Zn-1	H	H
Fe, Co, Ni, Cu, Zn-2	Br	H
Fe, Co, Ni, Cu, Zn-3	Br	Br
Fe, Co, Ni, Cu, Zn-4	Cl	H
Fe, Co, Ni, Cu, Zn-5	Cl	Cl

Table 1 Crystal data and structure refinement for Cu-1, Cu-3, and Zn-2.

	Cu-1	Cu-3	Zn-2
Formula	C ₃₀ H ₂₂ CuN ₂ O ₆	C ₃₀ H ₁₈ Br ₄ CuN ₂ O ₆	C ₃₀ H ₂₀ Br ₂ ZnN ₂ O ₆
Formula weight	570.65	885.64	729.71
Crystal system	Monoclinic	Monoclinic	Monoclinic
Space group	<i>P</i> 2 ₁	<i>P</i> 2 ₁	<i>P</i> 2 ₁
<i>Z</i>	2	2	2
<i>a</i> (Å)	16.286 (5)	15.802 (3)	20.07 (6)
<i>b</i> (Å)	21.506 (5)	18.098 (6)	10.01 (3)
<i>c</i> (Å)	10.1880 (13)	15.294 (4)	11.58 (3)
β (°)	101.39 (3)	114.352 (15)	112.67 (18)
<i>V</i> (Å ³)	3498.04 (2)	3984.7	2147 (10)
<i>R</i> _{wp} (%)	2.32	3.47	9.29

Fig. 2 Molecular structures of Cu-1 showing the selected atom-labeling scheme.

Table 2 Selected bond lengths (Å) and angles (°) for Cu-1.

Cu1-O1	1.9123 (6)	O1-Cu1-O3	93.23 (2)
Cu1-O3	1.9189 (3)	O1-Cu1-N1	92.39 (2)
Cu1-N1	1.9838 (4)	O1-Cu1-N2	171.047 (4)
Cu1-N2	1.9785 (7)	O3-Cu1-N1	171.011 (2)
		O3-Cu1-N2	92.35 (2)
		N1-Cu1-N2	82.97 (2)

asymmetric unit of Cu-3 contains a crystallographically independent molecule of four coordinated mononuclear Cu(II) complexes. Cu(II) complex affords a four-coordinated planar $[\text{CuN}_2\text{O}_2]$ geometry, with the four donor atoms of the tetradentate Schiff base forming the equatorial plane and the axial sites with Cu1-O1, Cu1-O3, Cu1-N1, and Cu1-N2 distances ranging from about 1.91 to 1.98 Å (Table 2). The chiral 4,4'-((1*S*,2*S*)-1,2-diammonioethane-1,2-diyl) dibenzoate moiety adopts a λ configuration with torsion angle C5-C4-C11-C12 = 155.9 (2)°.

The complex Cu-3 crystallizes in monoclinic, space group $P2_1$ with $Z = 2$. As shown in Fig. 3, the asymmetric unit of Cu-3 contains a crystallographically independent molecule of four coordinated mononuclear Cu(II) complexes. Cu(II) complex affords a four-coordinated square planar $[\text{CuN}_2\text{O}_2]$ geometry, with the four donor atoms of the tetradentate Schiff base forming the equatorial plane

and the axial sites with Cu1-O1, Cu1-O2, Cu1-N1, and Cu1-N2 distances ranging from about 1.91 to 1.98 Å (Table 3). The chiral 4,4'-((1*S*,2*S*)-1,2-diammonioethane-1,2-diyl) dibenzoate moiety adopts a λ configuration with torsion angle C3-C2-C23-C24 = 64.1 (2)°.

The Zn-2 complex crystallizes in monoclinic, space group $P2_1$ with $Z = 2$ (Table 4). As shown in Fig. 4, the asymmetric unit of Zn-2 contains a crystallographically independent molecule of four coordinated mononuclear Zn(II) complexes. Zn(II) complex affords a four-coordinated planar $[\text{ZnN}_2\text{O}_2]$ geometry, with the four donor atoms of the tetradentate Schiff base forming the distorted tetrahedron and the axial sites with Zn1-O1, Zn1-O2, Zn1-N1, and Zn1-N2 distances ranging from about 1.92 to 1.98 Å (Table 4). The chiral 4,4'-((1*S*,2*S*)-1,2-diammonioethane-1,2-diyl) dibenzoate moiety adopts a λ configuration with torsion angle C3-C2-C23-C24 = 51.4 (2)°.

Fig. 3 Molecular structures of Cu-3 showing the selected atom-labeling scheme.

Table 3 Selected bond lengths (Å) and angles (°) for Cu-3.

Cu1-O1	1.9161 (4)	O1-Cu1-O2	91.478 (16)
Cu1-O2	1.9170 (5)	O1-Cu1-N1	172.981 (2)
Cu1-N1	1.9816 (4)	O1-Cu1-N2	92.628 (15)
Cu1-N2	1.9830 (5)	O2-Cu1-N1	92.619 (16)
		O2-Cu1-N2	172.9786 (17)
		N1-Cu1-N2	83.884 (16)

Fig. 4 Molecular structures of Zn-2 showing the selected atom-labeling scheme.

Table 4 Selected bond lengths (Å) and angles (°) for Zn-2.

Zn1-O1	2.000 (5)	O1-Zn1-O2	114.4 (2)
Zn1-O2	1.960 (6)	O1-Zn1-N1	155.08 (6)
Zn1-N1	2.063 (4)	O1-Zn1-N2	83.4 (2)
Zn1-N2	2.021 (6)	O2-Zn1-N1	82.7 (2)
		O2-Zn1-N2	154.36 (8)
		N1-Zn1-N2	87.4 (2)

Fig. 5 CD and UV-Vis spectra of Fe-1, Co-1, Ni-1, Cu-1, and Zn-1 in DMSO solutions.

3.4 CD and UV-vis Spectra

The UV-vis absorption spectra of series dyes are depicted in Fig. 5 and Figs. S1, S2, S3, S4, S5. By comparing the electronic spectra of these complexes, the effect of the substituent and metal has been evaluated. All complexes exhibit three absorption bands in the 250-750 nm range. The high-energy region at 250-280 nm can be attributed to $\pi-\pi^*$

electron transitions of the ligand backbone, while the low-energy region at 350-550 nm can be ascribed to the MLCT (metal-to-ligand charge transfer) transitions. Among the complexes of the same metal, these d-d bands and CT bands showed a similar red-shift (Table 5, Figs. S1, S2, S3, S4, S5). Obviously, these shifts are correlated with the substituent. The effects of the substituent on the absorption spectra have been interpreted by correlation of absorption frequencies with Hammett

equations [26]. In the complexes of the same ligand, absorption intensity and wavelength differed by metal (Fig. 5). Absorption intensities of $\pi-\pi^*$ transition are in the order of Ni > Fe > Co > Cu. CT bands are in the order of Fe > Zn > Ni > Co > Cu. In particular, complexes of Fe and Ni have large absorption intensity and wide absorption range in these complexes.

3.5 Redox Potential

The electrochemical properties of Fe, Co, Ni, and Cu complexes were determined using CV (cyclic voltammetry), and are presented in Table 6 and Fig. 6. It can be seen that the energy level for the CB (conduction band) of TiO₂ was located between that of the LUMOs (lowest unoccupied molecular orbital) and HOMOs (highest occupied molecular orbital) of the complexes. Energy levels of LUMOs of the all

complexes with higher than the CB minimum of TiO₂ (-0.500 V), while energy levels of HOMOs of the all complexes were lower than the I³⁻/I potential of TiO₂ (+0.400 V). Therefore, all complexes should be able to dope electrons in TiO₂ and undergo regeneration. In addition, the electro chemical behavior of all complexes was reversible and the current values remained unchanged after repeated CV cycles, indicating that the complexes retain their structures. Next, the authors compared redox potential of complexes Fe-1, Co-1, Ni-1, and Cu-1 that they have Fe, Co, Ni and Cu for the central metal, respectively. They show E_{red} (Co > Ni > Cu > Fe), E_{ox} (Co > Ni > Cu > Fe) and HOMO-LUMO gap E_g (Fe > Co > Ni > Cu), respectively, in Fig. 6. Therefore, it can be concluded that the central metal participated in the MLCT transitions.

Table 5 Summary of electronic transitions in complexes.

	In DMSO		Solid state			
	CT [nm] (UV-Vis)	CT [nm] (CD)	CT [nm] (UV-Vis)	CT [nm] (CD)	d-d [nm] (UV-Vis)	d-d [nm] (CD)
Fe-1	322	343	351	370	503	513
Fe-2	338	341	362	372	521	497
Fe-3	335	344	357	381	522	510
Fe-4	323	345	367	381	513	508
Fe-5	328	342	368	363	514	505
Co-1	395	391	386	388	590	612
Co-2	398	392	399	391	602	613
Co-3	402	393	412	399	604	624
Co-4	394	390	400	390	596	606
Co-5	405	393	414	403	606	636
Ni-1	418	412	450	420	546	586
Ni-2	420	413	414	420	566	562
Ni-3	426	419	436	430	566	599
Ni-4	420	409	434	418	568	573
Ni-5	424	419	430	433	572	603
Cu-1	372	381	366	360	614	664
Cu-2	384	381	394	372	612	704
Cu-3	394	381	392	381	616	688
Cu-4	382	389	384	384	658	658
Cu-5	386	377	400	374	626	704
Zn-1	368	396	347	358	-	-
Zn-2	390	396	375	361	-	-
Zn-3	381	406	377	365	-	-
Zn-4	383	392	362	360	-	-
Zn-5	381	402	386	366	-	-

Table 6 Electrochemical measurement of chiral salen complexes.

	E_{ox} [V vs. NHE]	E_{red} [V vs. NHE]	$E_g(E_{ox}-E_{red})$ [V]	HOMO-LUMO gap [eV (TD-DFT)]
Fe-1	1.069	-1.248	2.317	3.772
Fe-2	1.121	-0.810	1.931	3.740
Fe-3	1.068	-0.728	1.796	3.800
Fe-4	1.073	-1.197	2.270	3.738
Fe-5	1.049	-1.217	2.266	3.791
Co-1	0.947	-0.706	1.652	3.638
Co-2	0.937	-0.688	1.625	3.552
Co-3	0.922	-0.687	1.609	3.477
Co-4	0.932	-0.680	1.612	3.554
Co-5	0.918	-0.690	1.605	3.491
Ni-1	0.789	-0.798	1.587	3.500
Ni-2	0.808	-0.928	1.736	3.430
Ni-3	0.794	-0.798	1.592	3.384
Ni-4	0.786	-0.788	1.574	3.428
Ni-5	0.759	-0.798	1.557	3.386
Cu-1	0.462	-0.847	1.309	2.825
Cu-2	0.486	-0.832	1.318	2.648
Cu-3	0.512	-0.753	1.265	2.624
Cu-4	0.902	-0.828	1.730	2.763
Cu-5	0.522	-0.792	1.314	2.643

Fig. 6 Energy level of Fe, Co, Ni, and Cu complexes.

3.6 Fluorescence Spectra of Zn Complexes.

As Zn(II) complexes have $3d^{10}$ electron, UV-Vis and CV are mentioned independently from complexes having other metals in this paper. Fig. 7 depicts the fluorescence spectra of Zn-(1-5), whose excitation wavelengths $\lambda_{ex} = 380$ nm are determined according to the wavelengths of the intense peaks of the UV-Vis absorption spectra mentioned above. For excitation at $\lambda_{ex} = 380$ nm, emission peaks appeared at $\lambda_{em} = 465, 470, 472, 469$ and 475 nm for Zn-(1-5), respectively. The fluorescence wavelength shifted long in the order

of Zn-5 > Zn-3 > Zn-2 > Zn-4 > Zn-1.

3.7 Computational Results

To rationalize the importance of the molecular electronic structures associated with the X- and Y-substituent groups in Fe, Co, Ni, Cu and Zn-(1-5), simulated UV-Vis and CD spectra, and the molecular orbitals of the ground and excited states, and electron density distribution of complexes were calculated for each complex. The results of Ni-(1-5) are shown in Figs. 8-12, respectively.

Fig. 7 Fluorescence spectra ($\lambda_{\text{ex}} = 380 \text{ nm}$) of Zn complexes in DMSO solutions.

Fig. 8 (a) Simulated CD spectra, (b) simulated UV-Vis spectra, (c) molecular orbitals of the ground state (HOMO) and excited state (LUMO+3), and (d) electron density distribution of Ni-1.

Fig. 9 (a) Simulated UV-Vis spectra, (b) simulated CD spectra, (c) molecular orbitals of the ground state (HOMO) and excited state (LUMO+3), and (d) electron density distribution of Ni-3.

In the complexes, the predominant absorption bands were assigned as transitions from the HOMO to the LUMO, which is distributed on the amine moieties. Based on these results, it is reasonable to conclude that the spectral shifts were due to the substitution of the X- and Y-groups. The electron transfers in all of the complexes occurred from metal and benzene derived from aldehyde, to benzenes derived from diamine and carboxyl group. In addition, after electron transfer, the electron density was distributed on the carboxyl groups through a six-membered ring. For example, according to the molecular orbitals for the ground state (HOMO) and excited state (LUMO+3) of Ni-1 (Fig. 8b), these electron transfers are MLCT. Therefore, it can be concluded that the electrons were transferred from the Ni(II) salen complexes to TiO₂. This tendency is also present with other complexes. Figs. S6, S7, S8, S9, S10, S11, S12, S13, S14, S15, S16, S17, S18, S19, S20, S21, S22, S23, S24, S25

show simulated CD and UV-Vis spectra of Fe, Co, and Cu complexes.

Table 6 summarizes the energy levels, redox potentials, and calculated HOMO-LUMO gaps for MLCT of compounds Fe, Co, Ni, and Cu-(1-5). In addition, the correlation between the π - π^* , MLCT band is shown in Fig. 8c. The relationships between the wavelength of the π - π^* , MLCT band correlated well for both the measured and calculated values obtained via TD-DFT. In particular, the HOMO-LUMO gap decreased as the wavelength became longer. In addition, the central metal had a noticeable effect on the differences in the values obtained for the HOMO-LUMO gaps via TD-DFT calculations and experimentally. They show the HOMO-LUMO gap (Fe > Co > Ni > Cu). The calculated values exhibit a trend due to substituent effects with electron withdrawing groups causing a decrease of the HOMO-LUMO gap.

Table 7 shows calculation of the HOMO-LUMO gap (ΔE_g), absorption wavelength (λ), oscillator strength (f), and transition assignment from the ground state to the excited state. In almost all of the metal complexes, the absorption wavelength shifted to become longer. These calculation results exhibit a similar tendency to the experimental results.

Table 8 presents the electric transition dipole moment of Fe, Co, Ni, Cu, and Zn-(1-5) obtained via TD-DFT. The calculated values show a trend due to substituent effects with electron withdrawing groups causing an increase of value of their dipole moment to carboxyl groups. In fact, more electrons of Ni-3 transfer to carboxyl groups than that of Ni-1 (Fig. 8b). This tendency is also present with other complexes. From this result, substituent effects with electron withdrawing groups may cause increases of the transfer of electrons to TiO_2 and of J_{sc} of DSSC.

3.8 XPS Measurement

The authors measured some Cu(II) and Zn(II) complexes adsorbed on titanium oxide by XPS measurement and analyzed the adsorption state of complexes. Samples were prepared on ITO substrates. TiO_2 paste involving polyethylene glycol (molecular weight 2000) was coated on an indium dope tin-oxide (ITO) using a spin-coat method. The ITO glass supporting TiO_2 film (0.25 cm^2) was then sintered at 723 K for 1 h. The electrode was immersed immediately into the dye solution (0.5 M, DMSO, 24 h) when the oven temperature was cooled to 313 K.

First, in order to compare the presence or absence of the carboxyl group, the authors measured Cu-1' + TiO_2 (Cu-1' = (1*R*,2*R*)-diphenyl salen Cu(II) complex (Fig. 10)) and Cu-1 + TiO_2 , by Ti 2p. As a result, chemisorption of Cu-1, Cu-5 was confirmed by

Table 7 Calculation values of complexes.

	E_g (eV)	Wavelength (nm)	f	Transition assignments
Fe-1	3.7715	329	0.1448	HOMO-2→LUMO+3
Fe-2	3.7396	332	0.2588	HOMO-2→LUMO+3
Fe-3	3.8002	326	0.5652	HOMO→LUMO+4
Fe-4	3.7378	332	0.2449	HOMO-2→LUMO+3
Fe-5	3.791	327	0.6812	HOMO→LUMO+4
Co-1	3.6382	341	0.2584	HOMO→LUMO+3
Co-2	3.5518	349	0.2433	HOMO→LUMO
Co-3	3.4773	357	0.2703	HOMO→LUMO
Co-4	3.5537	349	0.2515	HOMO→LUMO+2
Co-5	3.4914	355	0.2662	HOMO→LUMO+3
Ni-1	3.5003	354	0.2406	HOMO→LUMO+3
Ni-2	3.4301	361	0.2274	HOMO→LUMO
Ni-3	3.3838	366	0.2561	HOMO→LUMO+3
Ni-4	3.4279	362	0.2339	HOMO→LUMO+3
Ni-5	3.3856	366	0.2506	HOMO→LUMO+3
Cu-1	3.2825	378	0.0471	HOMO→LUMO+3
Cu-2	3.3643	369	0.0490	HOMO-1→LUMO+1
Cu-3	3.1321	396	0.0855	HOMO-1→LUMO+1
Cu-4	3.3362	372	0.0723	HOMO-1→LUMO+1
Cu-5	3.155	393	0.0783	HOMO→LUMO+3
Zn-1	3.6043	344	0.1362	HOMO→LUMO+3
Zn-2	3.3443	371	0.1108	HOMO-1→LUMO+1
Zn-3	3.2339	383	0.1238	HOMO-1→LUMO+1
Zn-4	3.2965	376	0.1037	HOMO-1→LUMO+1
Zn-5	3.2050	387	0.1153	HOMO-1→LUMO+1

Table 8 Directions (*x*, *y*, *z*) and magnitude (*D*) of dipole moments of complexes.

	<i>x</i>	<i>y</i>	<i>z</i>	Dipole moment [<i>D</i>]
Fe-1	-4.7892	0.0852	0.4897	4.8149
Fe-2	0.1917	5.5356	-0.0345	5.5390
Fe-3	0.0033	8.5350	-0.0009	8.5350
Fe-4	-0.4503	5.4847	-0.0515	5.5034
Fe-5	8.6997	-0.0208	0.0008	8.6997
Co-1	-5.4366	0.0000	0.0000	5.4366
Co-2	0.0000	-6.1636	0.0000	6.1636
Co-3	0.0000	-9.5384	0.0000	9.5384
Co-4	0.0000	-6.1089	0.0000	6.1089
Co-5	9.5163	-0.0001	0.0000	9.5163
Ni-1	5.6161	0.0000	0.0000	5.6161
Ni-2	-0.0000	-6.3779	0.0000	6.3779
Ni-3	0.0000	-9.7289	-0.0000	9.7289
Ni-4	-0.0000	-6.3267	-0.0000	6.3267
Ni-5	-9.7195	-0.0000	0.0000	9.7195
Cu-1	0.0240	-0.7273	-6.8475	6.8861
Cu-2	0.0000	0.0000	7.2553	7.2553
Cu-3	0.0000	9.4245	0.0000	9.4245
Cu-4	0.0000	6.0791	0.0000	6.0791
Cu-5	-9.5627	-0.0014	-0.0002	9.5627
Zn-1	4.6894	0.0000	0.0000	4.6894
Zn-2	0.4155	4.4865	-2.4330	5.1154
Zn-3	0.0000	-8.4376	0.0000	8.4376
Zn-4	0.0000	-4.7296	0.0000	4.7296
Zn-5	0.0000	8.0633	0.0000	8.0633

Fig. 10 Structure of Cu-1' (for comparison with no –COOH groups).

peak shift for TiO₂ (Fig. 11). The authors then measured (Cu-(1-5) + TiO₂) and compared the substituent effects. It was found that chemisorption of all complexes was confirmed by peak shift.

Since high-energy shifts more in the electron with drawing group, the authors compared the dipole moment of the complexes (TD-DFT calculation) and Ti 2p_{3/2}, as shown in Table 9. A tendency was observed towards a more high-energy shift from the larger dipole moment of complexes. Change of the

dipole moment due to the chemical adsorption affects the electronic state of the TiO₂ [27].

Next, in order to investigate the differences in adsorption structure according to the difference of amine moiety, the authors measured Zn-1 + TiO₂, Zn-6 + TiO₂ (Fig. 12), and TiO₂ at Ti 2p (Fig. 13). As a result, the one with the complex adsorbed shifted to the higher energy side than TiO₂ (Table 10). In addition, Zn-1 was shifted to a higher energy side than Zn-6. The authors thought that this was the result of

Fig. 11 XPS spectra of Ti 2p states for complexes (Cu-1', Cu-1) adsorbed on TiO₂, XPS spectra of Ti 2p states for Cu-(1-5) adsorbed on TiO₂.

Table 9 Comparison of peaks of Ti 2p_{3/2} for complexes on TiO₂ and dipole moment (TD-DFT).

	Ti 2p _{3/2} /ev	Dipole moment/D
Cu-1+TiO ₂	459.0	6.8861
Cu-2+TiO ₂	459.2	7.2553
Cu-3+TiO ₂	459.4	9.4245
Cu-4+TiO ₂	459.1	6.0791
Cu-5+TiO ₂	459.4	9.5627
TiO ₂	458.7

Fig. 15 Structure of Zn-6 (employing different amine moieties [21]).

the influence of core electrons by the deficiency of Ti electrons. This suggested that Ti and the O of the carboxyl group of the complex formed a chemical bond.

3.9 Photovoltaic Properties

Devices were prepared on ITO substrates. The TiO₂ film (active area 1.00 cm²) coat method was the squeegee method. It was then removed, washed with methanol, and dried in a desiccator. The solar cell was prepared by agglutinating the carbon counter electrode and the TiO₂ electrode. Electrolyte was injected and penetrated into the TiO₂ film. The electrolyte solution

was composed of I₂ (0.05 M), LiI (0.1 M), 1,2-dimethyl-3-propylimidazolium iodide (DMPI ml (0.6 M)), and 4-tert-butyl pyridine (TBP (0.3 M)) in acetonitrile. Photovoltaic characteristics of the DSSC based on the seven dyes, as well as a typical Ru dye N3 under air mass 1.5 global (AM 1.5 G) solar irradiation condition (100 mW·cm⁻²), are exhibited in Table 11.

To investigate the performance of the DSSCs with Fe-3, Co-3, Ni-1, Ni-3 and Cu-3, test cells were assembled according to procedures in the literature, and an electrolyte composition typically used for N3

was chosen. Conversion efficiency was in the order of $N3 > Cu-3 > Ni-3 > Ni-1 > Co-3 > Fe-3$ as shown Fig. 14. The power generation efficiency of salen dyes was smaller than that of N3. Change of J_{sc} was prominently visible in power conversion efficiency. Since the order of J_{sc} is $Ni-3 > Ni-1$, this result shows good agreement with the increase of their dipole moment to carboxyl groups. From the DSSC performances for N3, a need exists for optimization of the cells in the future.

IPCE and UV-Vis spectra of Cu-3 are shown Fig. 15. In IPCE, the peak of near 350 nm indicates photoelectric conversion by TiO_2 . The wavelength of photoelectric conversion corresponded to the absorption band of the complex. The photoelectric conversion by CT transition was broadened by changes in the electronic state of Cu-3. However, despite the results of TD-DFT, why IPCE was lower in CT was considered to constitute a low excitation lifetime due to not emitting light.

Fig. 13 XPS of TiO_2 film with selected Zn(II) complexes adsorption.

Table 10 Peak of $Ti\ 2p_{3/2}$ for complexes on TiO_2 and dipole moment (TD-DFT).

	$Ti\ 2p_{3/2}/ev$	Dipole moment/D
Zn-1 + TiO_2	459.2	4.6894
Zn-6 + TiO_2	459.1	4.5935
TiO_2	459.8	

Table 11 Comparison of the DSSC performances for Fe-3, Co-3, Ni-1, Ni-3, Cu-3, and N3 under $100\ mW\cdot cm^{-2}$ of AM 1.5 G.

	$V_{oc}\ (V)$	$J_{sc}\ (mA\cdot cm^{-2})$	ff ^a	$\eta\ (\%)$
Fe-3	0.04	0.0127	0.27	0.00015
Co-3	0.12	0.0260	0.28	0.00083
Ni-1	0.26	0.0411	0.36	0.00386
Ni-3	0.27	0.0511	0.36	0.00493
Cu-3	0.34	0.1117	0.31	0.01198
N3	0.61	2.2474	0.21	0.28872

^a Fill factor.

Fig. 14 J-V curve of Fe-3, Co-3, Ni-1, Ni-3 and Cu-3.

Fig. 15 IPCE of DSSC sensitized with Cu-3 and UV-Vis spectra (in DMSO solution).

4. Conclusion

The authors have designed and synthesized new chiral salen-type metal complexes M (M = Fe, Co, Ni, Cu, Zn-(1-5) for new conceptual dyes (co-sensitizer or colorful multi-dyes) and discussed the substituent effects on spectra. In CT bands and d-d bands, red-shift was observed by substituent effects.

According to CV measurement, reduction potentials

of Fe, Co, Ni, and Cu-(1-5) were lower than -0.5 V, which is electrochemically possible to dope electrons into TiO₂. In addition, the oxidation potential was higher than +0.4 V, which is electrochemically possible to regenerate a dye.

Chemisorption for TiO₂ of the complex by carboxyl groups was confirmed by XPS measurement. Preproduction DSSC with the dyes generated electricity. Substituent effects with electron

withdrawing groups caused increases of the value of their dipole moment to carboxyl groups and transfer of electrons to TiO_2 and J_{sc} of DSSC. Especially, complexes, including electron with drawing groups, exceeded power conversion efficiency (η). The results of η ($\text{Cu} > \text{Ni} > \text{Co} > \text{Fe}$) showed good agreement with the HOMO-LUMO gap ($\text{Fe} > \text{Co} > \text{Ni} > \text{Cu}$) by calculation.

Acknowledgements

The computations were performed using the Research Centre for Computational Science, Okazaki, Japan. This XRD work was conducted at the Advanced Characterization Nanotechnology Platform of the University of Tokyo (Prof. Kazuhiro Fukawa), supported by the Nanotechnology Platform of the Ministry of Education, Culture, Sports, Science and Technology (MEXT), Japan.

Supporting Information

The supplementary information can be downloaded from the journal website along with the article. CCDC1541109, 1541118, and 1537540 contain the supplementary crystallographic data for Cu-1, Cu-3, and Zn-2, respectively. These data can be obtained free of charge via <http://www.ccdc.cam.ac.uk/conts/retrieving.html>, or from the Cambridge Crystallographic Data Centre, 12 Union Road, Cambridge CB2 1EZ, UK; fax: (+44) 1223-336-033; or e-mail: deposit@ccdc.cam.ac.uk.

References

- [1] Harlang, T. C. B., Yizhu, L., Gordivska, O., and Fredin, L. A. 2015. "Iron Sensitizer Converts Light to Electrons with 92% Yield." *Nature Chemistry* 7 (October): 883-9.
- [2] Yeh, M. H., Hsu, H. R., Wang, K. C., Ho, S. J., Chen, G. H., and Chen, H. S. 2016. "Toward Low-Cost Large-Area CIGS Thin Film: Compositional and Structural Variations in Sequentially Electrodeposited CIGS Thin Films." *Sol. Energy* 125 (December): 415-25.
- [3] Fischer, G., and Torsten, W. 2014. "Simulation Based Development of Industrial PERC Cell Production beyond 20.5% Efficiency." *Energy Procedia* 55: 425-30.
- [4] Diouf, D., Kleider, J. P., Desruets, T., and Ribeyron, P. J. 2009. "Study of Interdigitated Back Contact Silicon Heterojunction Solar Cells by Two-Dimensional Numerical Simulations." *Mater. Sci. Eng. B* 159 (March): 291-4.
- [5] Fitzgerald, E. A., Xie, Y. H., and Monroe, D. 1992. "Relaxed $\text{Ge}_x\text{Si}_{1-x}$ Structures for III-V Integration with Si and High Mobility Two-Dimensional Electron Gases in Si." *J. Vac. Sci. Technol. B* 10 (July): 1807-9.
- [6] Sariciftci, N. S., Smilowitz, L., Heeger, A. J., and Wudl, F. 1992. "Photoinduced Electron Transfer from a Conducting Polymer to Buckminsterfullerene." *Science* 258 (November): 1474-6.
- [7] Moon, S. J., Itzhaik, Y., Yum, J. H., Zakeeruddin, S. M., Hodes, G., and Grätzel, M. 2010. "Sb₂S₃-Based Mesoscopic Solar Cell Using an Organic Hole Conductor." *J. Phys. Chem. Lett.* 1 (April): 1524-7.
- [8] Lee, H., Leventis, H. C., Moon, S. J., Chen, P., Ito, S., Haque, S. A., Torres, T., Nüesch, F., Geiger, T., Zakeeruddin, S. M., Grätzel, M., and Md. Nazeeruddin, M. K. 2009. "PbS and CdS Quantum Dot-Sensitized Solid-State Solar Cells: Old Concepts, New Results." *Adv. Funct. Mater* 19 (June): 2735-42.
- [9] O'Regan, B., and Grätzel, M. 1991. "A Low-Cost, High Efficiency Solar Cell Based on Dye-Sensitized Colloidal TiO_2 Films." *Nature* 353 (October): 737-9.
- [10] Kinoshita, T., Joanne, D. Y., Uchida, S., Kubo, T., and Segawa, H. 2013. "Wideband Dye-Sensitized Solar Cells Employing a Phosphine-Coordinated Ruthenium Sensitizer." *Nature Photonics* 7 (June): 535-9.
- [11] Bowman, D. N., Mukherjee, S., Barnes, L. J., and Jakubikova, E. 2015. "Linker Dependence of Interfacial Electron Transfer Rates in Fe(II)-Polypyridine Sensitized Solar Cells." *J. Phys. Condens. Matter* 27 (March): 134205.
- [12] Lu, X., Wu, C. H. L., Wei, S., and Guo, W. 2010. "DFT/TD-DFT Investigation of Electronic Structures and Spectra Properties of Cu-Based Dye Sensitizers." *J. Phys. Chem. A* 114 (December): 1178-4.
- [13] Nazeeruddin, M. K., Pechy, P., and Renouard, T. 2001. "Engineering of Efficient Panchromatic Sensitizers for Nanocrystalline TiO_2 -Based Solar Cells." *J. Am. Chem. Soc.* 123 (February): 1613-24.
- [14] Lee, K. E., Gomez, M. A., Regier, T., Hu, Y., and Demopoulos, G. 2011. "Further Understanding of the Electronic Interactions between N719 Sensitizer and Anatase TiO_2 Films: A Combined X-Ray Absorption and X-Ray Photoelectron Spectroscopic Study." *J. Phys. Chem. C* 115 (March): 5692-707.
- [15] Shahzad, N., Risplendi, F., and Pugliese, D. 2013. "Comparison of Hemi-Squaraine Sensitized TiO_2 and ZnO Photoanodes for DSSC Applications." *J. Phys. Chem. C* 117 (September): 22778-83.

- [16] Honda, M., Yanagida, M., Han, L., and Miyano, K. 2013. "X-Ray Characterization of Dye Adsorption in Coadsorbed Dye-Sensitized Solar Cells." *J. Phys. Chem. C* 117 (July): 17033-8.
- [17] Tanaka, H., Nishikawa, H., Uchida, T., and Katsuki, T. 2010. "Photopromoted Ru-Catalyzed Asymmetric Aerobic Sulfide Oxidation and Epoxidation Using Water as a Proton Transfer Mediator." *J. Am. Chem. Soc.* 132 (August): 12034-41.
- [18] Jia, Y., Gou, F., Fang, R., Jing, H., and Zhu, Z. 2014. "Salen Zn-Bridged D- π -A Dyes for Dye-Sensitized Solar Cells." *Chin. J. Chem.* 32 (April): 513-20.
- [19] Hwang, K. Y., Kim, H., Lee, Y. S., Lee, M. H., and Do, Y. 2009. "Synthesis and Properties of Salen-Aluminium Complexes as a Novel Class of Color-Tunable Luminophores." *Chem. Eur. J.* 15 (May): 6478-87.
- [20] Chiang, L., Harasymchuk, K., Thomas, F., and Storr, T. 2015. "Influence of Electron-Withdrawing Substituents on the Electronic Structure of Oxidized Ni and Cu Salen Complexes." *J. Am. Chem. Soc. Inorg. Chem.* 54 (May): 5970-80.
- [21] Shoji, R., Ikenomoto, S., Sunaga, N., Sugiyama, M., and Akitsu, T. 2016. "Absorption Wavelength Extension for Dye-Sensitized Solar Cells by Varying the Substituents of Chiral Salen Cu(II) Complexes." *J. Appl. Sol. Chem.* Model 5 (February): 48-56.
- [22] Kim, H., Nguyen Y., Yen, C. P. H., Chagal, L., Lough, A. J., Kim, B. M., and Chin, J. 2008. "Stereospecific Synthesis of C2 Symmetric Diamines from the Mother Diamine by Resonance-Assisted Hydrogen-Bond Directed Diaza-Cope Rearrangement." *J. Am. Chem. Soc.* 130 (June): 12184-91.
- [23] Numata, T., Ikenomoto, S., and Akitsu, T. 2016. "4,4'-(1,2-Diazaniumylethane-1,2-Diyl)Dibenzoate Trihydrate." *IUCrData* 1 (February): 160252.
- [24] Frisch, M. J., Trucks, G. W., Schlegel, H. B., Scuseria, G. E., Robb, M. A., Cheeseman, J. R., Scalmani, G., and Barone, V. et al. 2009. *Gaussian 09, Revision D.01*. Wallingford CT: Gaussian, Inc.
- [25] Rietveld, H. M. 1968. "A Profile Refinement Method for Nuclear and Magnetic Structures." *J. Appl. Crystallogr.* 2 (November): 65-71.
- [26] Suganya, K., and Kabilan, S. 2004. "Substituent and Solvent Effects on Electronic Absorption Spectra of Some N-(Substitutedphenyl) Benzene Sulphonamides." *Spectrochimica Acta* 60 (April): 1225-8.
- [27] Ozawa, H., Tawaraya, Y., and Arakawa, H. 2015. "Effects of the Alkyl Chain Length of Imidazolium Iodide in the Electrolyte Solution on the Performance of Black-Dye-Based Dye-Sensitized Solar Cells." *Electrochimica Acta* 151 (January): 447-52.